


Organic Light Emitting Diode (OLED)

Hole Transport Layer / Electron Blocking Layer (HTL/EBL) Materials

LT-E101 | NPB

N,N'-Bis(naphthalen-1-yl)-*N,N'*-bis(phenyl)-benzidine


CAS No. : 123847-85-8
Grade : Sublimed, > 99.5% (HPLC)
Formula : $C_{44}H_{32}N_2$
M.W. : 588.74 g/mole
UV : 339 nm (in THF)
PL : 450 nm (in THF)
TGA : > 350 °C (0.5% weight loss)



LT-E102 | β -NPB

N,N'-Bis(naphthalen-2-yl)-*N,N'*-bis(phenyl)-benzidine


CAS No. : 139255-17-7
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{44}H_{32}N_2$
M.W. : 588.74 g/mole
UV : 349 nm (in THF)
PL : 416 nm (in THF)
TGA : > 330 °C (0.5% weight loss)



LT-E103 | TPD

N,N'-Bis(3-methylphenyl)-*N,N'*-bis(phenyl)-benzidine


CAS No. : 65181-78-4
Grade : Sublimed, > 99.5% (HPLC)
Formula : $C_{38}H_{32}N_2$
M.W. : 516.67 g/mole
UV : 352 nm (in THF)
PL : 398 nm (in THF)
TGA : > 260 °C (0.5% weight loss)



LT-E105 | Spiro-TPD

N,N'-Bis(3-methylphenyl)-*N,N'*-bis(phenyl)-2,7-diamino-9,9-spirobifluorene


CAS No. : 1033035-83-4
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{51}H_{38}N_2$
M.W. : 678.86 g/mole
UV : 379 nm (in THF)
PL : 416 nm (in THF)
TGA : > 280 °C (0.5% weight loss)



LT-E106 | Spiro-NPB

N,N'-Bis(naphthalen-1-yl)-*N,N'*-bis(phenyl)-2,7-diamino-9,9-spirobifluorene


CAS No. : 932739-76-9
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{57}H_{38}N_2$
M.W. : 750.93 g/mole
UV : 380 nm (in THF)
PL : 453 nm (in THF)
TGA : > 360 °C (0.5% weight loss)



LT-E109 | DMFL-TPD

N,N'-Bis(3-methylphenyl)-*N,N'*-bis(phenyl)-2,7-diamino-9,9-dimethyl-fluorene

CAS No. : 677350-83-3
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{41}H_{36}N_2$
M.W. : 556.74 g/mole
UV : 376 nm (in THF)
PL : 401 nm (in THF)
TGA : > 290 °C (0.5% weight loss)




Organic Light Emitting Diode (OLED)

Hole Transport Layer / Electron Blocking Layer (HTL/EBL) Materials

LT-E110 | DMFL-NPB

N,N'-Bis(naphthalen-1-yl)-*N,N'*-bis(phenyl)-2,7-diamino-9,9-dimethyl-fluorene

CAS No. : 1229226-27-0
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{47}H_{36}N_2$
M.W. : 628.80 g/mole
UV : 381 nm (in THF)
PL : 458 nm (in THF)
TGA : > 330 °C (0.5% weight loss)



LT-E111 | DPFL-TPD

N,N'-Bis(3-methylphenyl)-*N,N'*-bis(phenyl)-2,7-diamino-9,9-diphenyl-fluorene


CAS No. : 206886-03-5
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{51}H_{40}N_2$
M.W. : 680.88 g/mole
UV : 381 nm (in THF)
PL : 410 nm (in THF)
TGA : > 320 °C (0.5% weight loss)



LT-E112 | DPFL-NPB

N,N'-Bis(naphthalen-1-yl)-*N,N'*-bis(phenyl)-2,7-diamino-9,9-diphenyl-fluorene


CAS No. : 357645-40-0
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{57}H_{40}N_2$
M.W. : 752.94 g/mole
UV : 371 nm (in THF)
PL : 466 nm (in THF)
TGA : > 300 °C (0.5% weight loss)



LT-E115 | α -NPD

N,N'-Bis(naphthalen-1-yl)-*N,N'*-bis(phenyl)-2,2'-dimethylbenzidine


CAS No. : 495416-60-9
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{46}H_{36}N_2$
M.W. : 616.79 g/mole
UV : 307 nm (in THF)
PL : 447 nm (in THF)
TGA : > 310 °C (0.5% weight loss)



LT-E116 | Spiro-TAD

2,2',7,7'-Tetrakis(*N,N*-diphenylamino)-2,7-diamino-9,9-spirobifluorene


CAS No. : 189363-47-1
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{73}H_{52}N_4$
M.W. : 985.22 g/mole
UV : 378 nm (in THF)
PL : 415 nm (in THF)
TGA : > 290 °C (0.5% weight loss)



LT-N121 | NPAPF

9,9-Bis[4-(*N,N*-bis-naphthalen-2-yl-amino)phenyl]-9H-fluorene

CAS No. : 916061-87-5
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{65}H_{44}N_2$
M.W. : 853.06 g/mole
UV : 322 nm (in THF)
PL : 418 nm (in THF)
TGA : > 400 °C (0.5% weight loss)




Organic Light Emitting Diode (OLED)

Hole Transport Layer / Electron Blocking Layer (HTL/EBL) Materials

LT-N124 | NPBAF

9,9-Bis[4-(*N*-naphthalen-1-yl-*N*'-phenylamino)-phenyl]-9*H*-fluorene


CAS No. : 510775-24-3
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{57}H_{40}N_2$
M.W. : 752.94 g/mole
UV : 304 nm (in THF)
PL : 431 nm (in THF)
TGA : > 320 °C (0.5% weight loss)



LT-N125 | Spiro-2NPB

2,2',7,7'-Tetrakis[*N*-naphthalenyl(phenyl)-amino]-9,9-spirobifluorene


CAS No. : 404001-42-9
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{89}H_{60}N_4$
M.W. : 1185.46 g/mole
UV : 380 nm (in THF)
PL : 484 nm (in THF)
TGA : > 420 °C (0.5% weight loss)



LT-N131 | PAPB

N,N'-Bis(phenanthren-9-yl)-*N,N'*-bis(phenyl)-benzidine


CAS No. : 934000-87-0
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{52}H_{36}N_2$
M.W. : 688.86 g/mole
UV : 336 nm (in THF)
PL : 454 nm (in THF)
TGA : > 410 °C (0.5% weight loss)



LT-N135 | 2,2'-Spiro-DBP

2,2'-Bis[*N,N'*-bis(biphenyl-4-yl)amino]-9,9-spirobifluorene


CAS No. : 1174006-39-3
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{73}H_{50}N_2$
M.W. : 955.19 g/mole
UV : 349 nm (in THF)
PL : 413 nm (in THF)
TGA : > 310 °C (0.5% weight loss)



LT-N136 | Spiro-BPA

2,2'-Bis[*N,N'*-di-phenyl-amino]-9,9-spirobifluorene


CAS No. : 862664-73-1
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{49}H_{34}N_2$
M.W. : 650.81 g/mole
UV : 348 nm (in THF)
PL : 398 nm (in THF)
TGA : > 310 °C (0.5% weight loss)
Reference : *Adv. Mater.* 2006, 18, 1216-1220.



LT-N137 | TAPC

Di-[4-(*N,N'*-di-*p*-tolyl-amino)-phenyl]cyclohexane

CAS No. : 58473-78-2
Grade : Sublimed, > 99.5% (HPLC)
Formula : $C_{46}H_{46}N_2$
M.W. : 626.87 g/mole
UV : 305 nm (in THF)
PL : 414 nm (in THF)
TGA : > 290 °C (0.5% weight loss)
Reference : *Journal of Applied Physics*, Vol. 95, No. 12, 7798




LT-N138 | Spiro-TTB

2,2',7,7'-Tetra(*N,N*-di-*p*-tolyl)amino-9,9-spirobifluorene

CAS No. : 515834-67-0
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{81}H_{68}N_4$
 M.W. : 1097.43 g/mole
 UV : 385 nm (in THF)
 PL : 409 nm (in THF)
 TGA : > 360 °C (0.5% weight loss)


Reference : *Adv. Funct. Mater.* 2006, 16, 966-974.



LT-N139 | β -TNB

N,N,N',N'-Tetra-naphthalen-2-yl-benzidine


CAS No. : 141752-82-1
 Grade : Sublimed, > 98% (HPLC)
 Formula : $C_{52}H_{36}N_2$
 M.W. : 688.86 g/mole
 UV : 354 nm (in THF)
 PL : 429 nm (in THF)
 TGA : > 410 °C (0.5% weight loss)



LT-N140 | HMTPD

N,N,N',N'-Tetra-(3-methylphenyl)-3,3'-dimethylbenzidine


CAS No. : 105465-14-3
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{42}H_{40}N_2$
 M.W. : 572.78 g/mole
 UV : 302 nm (in THF)
 PL : 399 nm (in THF)
 TGA : > 240 °C (0.5% weight loss)



LT-N141 | α,β -TNB

N,N'-Di(naphthalenyl)-*N,N'*-di(naphthalen-2-yl)-benzidine


CAS No. : 374592-88-8
 Grade : Sublimed, > 98% (HPLC)
 Formula : $C_{52}H_{36}N_2$
 M.W. : 688.86 g/mole
 UV : 345 nm (in CH_2Cl_2)
 PL : 462 nm (in CH_2Cl_2)
 TGA : > 370 °C (0.5% weight loss)



LT-N142 | α -TNB

N,N,N',N'-Tetra-naphthalenyl-benzidine


CAS No. : 186256-01-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{52}H_{36}N_2$
 M.W. : 688.86 g/mole
 UV : 297,362 nm (in CH_2Cl_2)
 PL : 462 nm (in CH_2Cl_2)
 TGA : > 360 °C (0.5% weight loss)



LT-N143 | β -NPP

N,N'-Di(naphthalen-2-yl)-*N,N'*-diphenylbenzene-1,4-diamine

CAS No. : 139994-47-1
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{38}H_{28}N_2$
 M.W. : 512.64 g/mole
 UV : 323 nm (in THF)
 PL : 466 nm (in THF)
 TGA : > 270 °C (0.5% weight loss)




Organic Light Emitting Diode (OLED)

Hole Transport Layer / Electron Blocking Layer (HTL/EBL) Materials

LT-N144 | TTP

N,N'-Diphenyl-*N,N'*-di-*m*-tolylbenzene-1,4-diamine


CAS No. : 80223-29-6
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{32}H_{28}N_2$
M.W. : 440.58 g/mole
UV : 314 nm (in CH_2Cl_2)
PL : 439 nm (in CH_2Cl_2)
TGA : > 270 °C (0.5% weight loss)



LT-N145 | NDDP

N,N',N'',N'''-Tetraphenyl-naphthalene-2,6-diamine

CAS No. : 111961-87-6
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{34}H_{26}N_2$
M.W. : 462.58 g/mole
UV : 312, 341 nm (in CH_2Cl_2)
PL : 438 nm (in CH_2Cl_2)
TGA : > 290 °C (0.5% weight loss)




LT-N146 | TQTPA

Tris(4-(quinolin-8-yl)phenyl)amine

CAS No. : 1142945-07-0
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{45}H_{30}N_4$
M.W. : 626.75 g/mole
UV : 287, 368 nm (in CH_2Cl_2)
PL : 431 nm (in CH_2Cl_2)
TGA : > 390 °C (0.5% weight loss)

Reference : *Chem. Mater.* 2009, 21, 1284-1287




LT-N148 | TFB

Poly[(9,9-dioctylfluorenyl-2,7-diyl)-co-(4,4'-(*N*-(4-sec-butylphenyl) diphenylamine)]

CAS No. : 220797-16-0
Grade : $M_w > 30,000$ (GPC)
Formula : $(C_{51}H_{61}N)_n$
UV : 389 nm (in CH_2Cl_2)
PL : 443 nm (in CH_2Cl_2)
Solubility : Soluble in CH_2Cl_2 , Toluene, $CHCl_3$

Reference : *Synthetic Metals* 160 (2010) 2393-2396




LT-N149 | Poly-TPD

Poly[*N,N'*-bis(4-butylphenyl)-*N,N'*-bis(phenyl)-benzidine]

CAS No. : 472960-35-3
Grade : $M_w > 10,000$ (GPC)
Formula : $(C_{22}H_{21}N)_n$
UV : 371, 388 nm (in CH_2Cl_2)
PL : 424 nm (in CH_2Cl_2)
Solubility : Soluble in $CHCl_3$, Chlorobenzene


Reference : *J. Mater. Chem.*, 2012, 22, 22769-22773



LT-N151

*N*₄,*N*₄,*N*₄',*N*₄'-tetra([1,1'-biphenyl]-4-yl)-[1,1'-biphenyl]-4,4'-diamine


CAS No. : 164724-35-0
Grade : Sublimed, >99% (HPLC)
Formula : $C_{60}H_{44}N_2$
M.W. : 793 (g/mole)



LT-N154 | DOFL-NPB

N,N'-Di(naphthalen-1-yl)-9,9-dioctyl-*N,N'*-diphenyl-9H-fluorene-2,7-diamine


CAS No. : 870197-09-4
 Grade : > 99% (HPLC)
 Formula : $C_{61}H_{64}N_2$
 M.W. : 825.17 g/mole
 UV : 382 nm (in THF)
 PL : 460 nm (in THF)
 TGA : > 250 °C (0.5% weight loss)



LT-N155 | DOFL-TPD

N,N'-Bis(3-methylphenyl)-*N,N'*-bis(phenyl)-9,9-dioctyl-fluorene


CAS No. : 439942-97-9
 Grade : > 99% (HPLC)
 Formula : $C_{55}H_{64}N_2$
 M.W. : 753.11 g/mole
 UV : 376 nm (in THF)
 PL : 401 nm (in THF)
 TGA : > 250 °C (0.5% weight loss)



LT-N157 | VNPB

N,N'-Di(naphthalen-1-yl)-*N,N'*-bis(4-vinylphenyl)biphenyl-4,4'-diamine

CAS No. : 1010396-31-2
 Grade : > 95% (HPLC)
 Formula : $C_{48}H_{36}N_2$
 M.W. : 640.81 g/mole
 UV : 339 nm (in THF)
 PL : 450 nm (in THF)




LT-N158 | ONPB

N,N'-Di(naphthalen-1-yl)-*N'*-(4-octylphenyl)-*N''*-phenylbiphenyl-4,4'-diamine

CAS No. : 1431521-16-2
 Grade : > 99% (HPLC)
 Formula : $C_{52}H_{48}N_2$
 M.W. : 700.95 g/mole
 UV : 347 nm (film)
 PL : 439 nm (film)
 TGA : > 300 °C (0.5% weight loss)

Reference : *Journal of Photopolymer Science and Technology, Vol. 25, 3(2012) 335-339*




LT-N159 | OTPD

N,N'-Bis(4-(6-((3-ethyloxetan-3-yl)methoxy)hexyl)phenyl)-*N,N'*-diphenylbiphenyl-4,4'-diamine

CAS No. : 746634-00-4
 Grade : > 99% (HPLC)
 Formula : $C_{60}H_{72}N_2O_4$
 M.W. : 885.22 g/mole
 UV : 308, 353 nm (in CH_2Cl_2)
 PL : 410 nm (in CH_2Cl_2)

Reference : 1. *Adv. Mater.* 2006, 18, 948-954
 2. *Appl. Phys. Lett.* 91, 103507(2007)



Organic Light Emitting Diode (OLED)


Hole Transport Layer / Electron Blocking Layer (HTL/EBL) Materials

LT-N160 | QUPD

N,N'-Bis(4-(6-((3-ethyloxetan-3-yl)methoxy)hexyloxy)phenyl)-*N,N'*-bis(4-methoxyphenyl)biphenyl-4,4'-diamine

CAS No. : 864130-79-0
Grade : > 99% (HPLC)
Formula : $C_{62}H_{76}N_2O_8$
M.W. : 945.28 g/mole
UV : 353 nm (in CH_2Cl_2)
PL : 439 nm (in CH_2Cl_2)


Reference : 1. *Adv. Mater.* 2006, 18, 948-954
2. *Appl. Phys. Lett.* 91, 103507(2007)



LT-N162 | TCBCPA

4,4'-(Diphenylmethylene)bis(*N,N'*-diphenylaniline)

CAS No. : 1459723-98-8
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{49}H_{38}N_2$
M.W. : 654.84 g/mole
UV : 303 nm (in CH_2Cl_2)
PL : 374 nm (in CH_2Cl_2)
TGA : > 320 °C (0.5% weight loss)




LT-N164 | VB-FNPD

9,9-Bis[4-[(4-ethenylphenyl)methoxy]phenyl]-*N,N'*-di-1-naphthalenyl-*N,N'*-diphenyl-9*H*-fluorene-2,7-diamine

CAS No. : 1173170-48-3
Grade : > 95% (HPLC)
Formula : $C_{75}H_{56}N_2O_2$
M.W. : 1017.26 g/mole
UV : 356 nm (in CH_2Cl_2)
PL : 467 nm (in CH_2Cl_2)

Reference : *J. Mater. Chem.*, 2009, 19, 3618-3623




LT-N165 | X-F6-TAPC

N,N'-(4,4'-(Cyclohexane-1,1-diylo)bis(4,1-phenylene))bis(*N*-(4-(6-(2-ethyloxetan-2-yloxy)hexyl)phenyl)-3,4,5-trifluoroaniline)

Grade : > 99% (HPLC)
Formula : $C_{66}H_{76}F_6N_2O_4$
M.W. : 1075.33 g/mole
UV : 300 nm (in CH_2Cl_2)


Reference : *Adv. Funct. Mater.* 2013, 23, 359-365



LT-N1002 | BF-DPB

N,N'-Bis(9,9-dimethyl-9*H*-fluorene-2-yl)-*N,N'*-diphenylbiphenyl-4,4'-diamine

CAS No. : 361486-60-4
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{54}H_{44}N_2$
M.W. : 720.94 g/mole
UV : 365 nm (in CH_2Cl_2)
PL : 418 nm (in CH_2Cl_2)
TGA : > 250 °C (0.5% weight loss)




LT-N002 | Ir(ppz)₃

Tris(phenylpyrazole)iridium

CAS No. : 562824-31-1
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{27}H_{21}N_6Ir$
M.W. : 621.71 g/mole
UV : 242, 320 nm (in THF)
PL : 423 nm (in THF)
TGA : > 270 °C (0.5% weight loss)

Reference : 1. *Applied Physics Letters*, 86, 263502 (2005)
2. *Advanced Materials*, Volume 16, (2004)




Our products are used for testing and research purpose; they are not guaranteed in patent contention by customer use.

LT-N177 | PFN-OX

6,6'-(9,9'-Bis(6-((3-ethoxyhexan-3-yl)methoxy)hexyl)-7,7'-diphenyl-9H,9'H-2,2'-bifluorene-9,9-diyl)bis(N,N-diethylhexan-1-amine)

CAS No. : 1345045-27-3
 Grade : $M_w > 20,000$ (GPC)
 UV : 378 nm (in THF)
 Formula : $(C_{70}H_{102}N_2O_4)_n C_{12}H_{10}$
 Solubility : Soluble in THF, $CHCl_3$

Reference : *J. Mater. Chem. C*, 2014,2, 3270-3277




LT-N178 | TBA

Tri(biphenyl-4-yl)amine

CAS No. : 6543-20-0
 Grade : > 99% (HPLC)
 Formula : $C_{36}H_{27}N$
 M.W. : 473.61 g/mole
 TGA : > 150 °C (0.5% weight loss)

Reference : *Australian Journal of Chemistry* (2009), 62(5), 483-492




LT-N180 | Spiro-mTTB

2,2',7,7'-Octa(m-tolylamine)-9,9-spirobifluorene

CAS No. : 302344-41-8
 Grade : > 99% (HPLC)
 Formula : $C_{81}H_{68}N_4$
 M.W. : 1097.43 g/mole
 UV : 378 nm (in THF)
 PL : 415 nm (in THF)
 TGA : > 220 °C (0.5% weight loss)

Reference : 1. *J. Appl. Phys.* 100,064507(2006)


2. *Synthetic Metals*, 148(2005)205-211



LT-N181 | PFNIBT

Poly(9,9-bis(6-trimethyl ammoniumiodide)-hexyl-fluorene-2,7-diyl-*a*/t(benzo[2,1,3]thiadiazol-4,7-diyl))

Grade : $M_w > 20,000$ (GPC)
 Formula : $(C_{37}H_{50}I_2N_4S)_n$
 M.W. : 670.91 g/mole
 Solubility : Soluble in $CHCl_3$, Chlorobenzene, Dichlorobenzene




LT-N182 | TSBPA

4,4'-(Diphenylsilanediyl)bis(N,N-diphenylamine)

CAS No. : 205327-13-5
 Grade : > 99% (HPLC)
 Formula : $C_{48}H_{38}N_2Si$
 M.W. : 670.91 g/mole
 UV : 309 nm (in CH_2Cl_2)
 PL : 376 nm (in CH_2Cl_2)
 TGA : > 180 °C (0.5% weight loss)

Reference : *Synthetic Metals* (2013), 167, 1-4




Organic Light Emitting Diode (OLED)

Hole Transport Layer / Electron Blocking Layer (HTL/EBL) Materials

LT-N183 | DTAF

4,4'-(9H-fluoren-9-ylidene)bis[N,N-bis(4-methylphenyl)-benzenamine]


CAS No. : 159526-57-5
Grade : Sublimed, > 99%
Formula : $C_{53}H_{44}N_2$
M.W. : 708.93 g/mole
UV : 304 nm (in THF)
PL : 431 nm (in THF)
TGA : > 300 °C (0.5% weight loss)
Reference : Dalton Transactions (2015), 44(33), 14613-14624



LT-N184 | PCZAC

9,10-Dihydro-9,9-dimethyl-10-(9-phenyl-9H-carbazol-3-yl)-acridine


CAS No. : 1705584-08-2
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{33}H_{26}N_2$
M.W. : 450.57 g/mole



LT-N186 | 2,2'-HMTDP

2,2'-Dimethyl-N4,N4,N4',N4'-tetram-tolylbiphenyl-4,4'-diamine


CAS No. : 80730-98-9
Grade : Sublimed, >99% (HPLC)
Formula : $C_{42}H_{40}N_2$
M.W. : 572.78 (g/mole)



LT-N187


N4,N4-di(biphenyl-4-yl)-N4'-(naphthalen-1-yl)-N4'-phenyl-biphenyl-4,4'-diamine

CAS No. : 897671-42-0
Grade : Sublimed, >99% (HPLC)
Formula : $C_{52}H_{38}N_2$
M.W. : 690.87 (g/mole)




LT-N188 | DM-FTB

Formula : $(C_{49}H_{57}N)_n$
M.W. : 20-50 kDa



LT-N189 | iPrCN


Formula : $(C_{51}H_{58}N_2)_n$



LT-E201 | CuPC

Copper(II) phthalocyanine

CAS No. : 147-14-8
 Grade : Sublimed, > 99%
 Formula : $C_{22}H_{16}N_8Cu$
 M.W. : 576.07 g/mole
 UV : 345, 631 nm (in CH_2Cl_2)
 PL : 404 nm (film)
 TGA : > 430 °C (0.5% weight loss)




LT-E202 | m-MTDATA

4,4',4'' -Tris(*N*-3-methylphenyl-*N*-phenyl-amino) triphenylamine

CAS No. : 124729-98-2
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{57}H_{48}N_4$
 M.W. : 789.02 g/mole
 UV : 312, 342 nm (in THF)
 PL : 425 nm (in THF)
 TGA : > 350 °C (0.5% weight loss)

Reference : 1. *Journal of Nanoscience and Nanotechnology* (2014), 14(8), 6404-6408
 2. *Applied Mechanics and Materials* (2014), 536-537




LT-E203 | 2T-NATA

4,4',4'' -Tris(*N*-(naphthalen-2-yl)-*N*-phenyl-amino) triphenylamine

CAS No. : 185690-41-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{66}H_{48}N_4$
 M.W. : 897.11 g/mole
 UV : 326 nm (in THF)
 PL : 490 nm (in THF)
 TGA : > 350 °C (0.5% weight loss)

Reference : 1. *Journal of Nanoscience and Nanotechnology* (2014), 14(8), 6404-6408
 2. *Synthetic Metals* (2015), 203, 174-179




LT-E204 | 1T-NATA

4,4',4'' -Tris(*N*-(naphthalen-1-yl)-*N*-phenyl-amino) triphenylamine

CAS No. : 185690-39-5
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{66}H_{48}N_4$
 M.W. : 897.11 g/mole
 UV : 339 nm (in THF)
 PL : 518 nm (in THF)
 TGA : > 350 °C (0.5% weight loss)

Reference : 1. *Advanced Materials* (Weinheim, Germany) (2014), 26(6), 878-885
 2. *Organic Electronics* (2010), 11(4), 564-572



Organic Light Emitting Diode (OLED)


Hole Injection Layer(HIL) Materials

LT-E205 | NATA

4,4',4'' -Tris(*N,N*-diphenyl-amino)triphenylamine

CAS No. : 105389-36-4
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{54}H_{42}N_4$
M.W. : 746.94 g/mole
UV : 341 nm (in THF)
PL : 424 nm (in THF)
TGA : > 350 °C (0.5% weight loss)


Reference : 1. *Applied Physics Letters* (2004), 85(21), 4848-4850
2. *Advanced Functional Materials* (2001), 11(4), 310-314



LT-E206 | TiOPC

Titanium(IV) oxide phthalocyanine

CAS No. : 26201-32-1
Grade : Sublimed, > 99%
Formula : $C_{32}H_{16}N_8OTi$
M.W. : 576.39 g/mole
UV : 349, 689 nm (in CH_2Cl_2)
PL : 392 nm (in film)
TGA : > 440 °C (0.5% weight loss)




LT-E208 | F4-TCNQ

2,3,5,6-Tetrafluoro-7,7,8,8-tetracyano-quinodimethane

CAS No. : 29261-33-4
Grade : Sublimed, > 99%
Formula : $C_{12}F_4N_4$
M.W. : 276.15 g/mole
UV : 339 nm (in THF)
PL : 402 nm (in THF)
TGA : > 210 °C (0.5% weight loss)


Reference : *J. Appl. Phys.* 103, 043105(2008)



LT-N211 | PPDN

Pyrazino[2,3-*f*][1,10]phenanthroline-2,3-dicarbonitrile

CAS No. : 215611-93-1
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{16}H_6N_6$
M.W. : 282.26 g/mole
UV : 307 nm (in CH_2Cl_2)
PL : 487 nm (in CH_2Cl_2)
TGA : > 270 °C (0.5% weight loss)




LT-N212 | MeO-TPD

N,N,N',N'-Tetrakis(4-methoxyphenyl)benzidine

CAS No. : 122738-21-0
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{40}H_{36}N_2O_4$
M.W. : 608.72 g/mole
UV : 302, 351 nm (in THF)
PL : 429 nm (in THF)
TGA : > 300 °C (0.5% weight loss)


Reference : 1. *J. Appl. Phys.* 100, 064507(2006)
2. *Synthetic Metals*, 148(2005)205-211



LT-N213 | MeO-Spiro-TPD


2,7-Bis[*N,N*-bis(4-methoxy-phenyl)amino]-9,9-spirobifluorene

CAS No. : 1138220-69-5
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{53}H_{42}N_2O_4$
M.W. : 770.91 g/mole
UV : 306, 386 nm (in THF)
PL : 428 nm (in THF)
TGA : > 330 °C (0.5% weight loss)




LT-N214 | 2,2'-MeO-Spiro-TPD2,2'-Bis[*N,N*-bis(4-methoxy-phenyl)amino]-9,9-spirofluorene


CAS No. : 1174006-40-6
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{53}H_{42}N_2O_4$
 M.W. : 770.91 g/mole
 UV : 348 nm (in CH_2Cl_2)
 PL : 442 nm (in CH_2Cl_2)
 TGA : > 350 °C (0.5% weight loss)

**LT-N215** | NTNPB*N,N'*-Diphenyl-*N,N'*-di-[4-(*N,N*-di-*p*-tolyl-amino)phenyl]benzidine


CAS No. : 1394130-64-3
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{64}H_{54}N_4$
 M.W. : 879.14 g/mole
 UV : 327 nm (in THF)
 PL : 458 nm (in THF)
 TGA : > 350 °C (0.5% weight loss)

**LT-N216** | NPNPB*N,N'*-Diphenyl-*N,N'*-di-[4-(*N,N*-diphenyl-amino)phenyl]benzidine

CAS No. : 936355-01-0
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{60}H_{46}N_4$
 M.W. : 823.03 g/mole
 UV : 324 nm (in THF)
 PL : 451 nm (in THF)
 TGA : > 370 °C (0.5% weight loss)


**LT-N218** | TPT1*N,N'*-(Biphenyl-4,4'-diyl)bis(*N,N'*,*N''*-triphenylbiphenyl-4,4'-diamine)

CAS No. : 167218-46-4
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{72}H_{54}N_4$
 M.W. : 975.23 g/mole
 UV : 394 nm (in CH_2Cl_2)
 PL : 419 nm (in CH_2Cl_2)
 TGA : > 370 °C (0.5% weight loss)

**LT-N219** | PtPC


Platinum(II) phthalocyanine

CAS No. : 14075-08-2
 Grade : Sublimed, > 99%
 Formula : $C_{32}H_{16}N_8Pt$
 M.W. : 707.60 g/mole
 UV : 228, 270 nm (in CH_2Cl_2)
 PL : 372.5 nm (in CH_2Cl_2)
 TGA : > 460 °C (0.5% weight loss)




LT-N221 | HAT-CNDipyrazino[2,3-*f*,2',3'-*b'*]quinoxaline-2,3,6,7,10,11-hexacarbonitrile

CAS No. : 105598-27-4
 Grade : Sublimed, > 99% (HPLC)
 Formula : C₁₈N₁₂
 M.W. : 384.27 g/mole
 UV : 282, 321 nm (in CH₂Cl₂)
 PL : 422 nm (in CH₂Cl₂)
 TGA : > 400 °C (0.5% weight loss)


Reference : *J. Mater. Chem. C*, 2013, 1, 3967–3975**LT-N222 | H2PC**

Phthalocyanine


CAS No. : 574-93-6
 Grade : Sublimed product
 Formula : C₃₂H₁₈N₈
 M.W. : 514.54 g/mole
 UV : 693 nm (in C₆H₆)
 PL : 699 nm (in C₆H₆)

**LT-N224 | HATNA**Diquinoxalino[2,3-*a*:2',3'-*c*]phenazine


CAS No. : 214-83-5
 Grade : Sublimed, > 99% (HPLC)
 Formula : C₂₄H₁₂N₆
 M.W. : 384.39 g/mole
 UV : 295, 378 nm (in CH₂Cl₂)
 PL : 594 nm (in CH₂Cl₂)
 TGA : > 340 °C (0.5% weight loss)

Reference : *Chem. Eur. J.* 2007, 13, 3537 – 3547**LT-N225 | HATNA-Cl6**2,3,8,9,14,15-Hexachlorodiquinoxalino[2,3-*a*:2',3'-*c*]phenazine


CAS No. : 389121-44-2
 Grade : Sublimed, > 99% (HPLC)
 Formula : C₂₄H₆N₆Cl₆
 M.W. : 591.06 g/mole
 UV : 305 nm (in CH₂Cl₂)
 PL : 425 nm (in CH₂Cl₂)
 TGA : > 350 °C (0.5% weight loss)

Reference : *Chem. Eur. J.* 2007, 13, 3537 – 3547**LT-N226 | HATNA-F6**2,3,8,9,14,15-Hexafluorodiquinoxalino[2,3-*a*:2',3'-*c*]phenazine

CAS No. : 872140-95-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : C₂₄H₆N₆F₆
 M.W. : 492.34 g/mole
 UV : 285 nm (in CH₂Cl₂)
 PL : 427 nm (in CH₂Cl₂)

Reference : *Chem. Eur. J.* 2007, 13, 3537 – 3547**LT-N260 | 3FTPD-C8***N,N'*-(9,9-Dioctyl-9H-fluorene-2,7-diyl)bis(9,9-dimethyl-*N,N'*-triphenyl-9H-fluorene-2,7-diamine)


Grade : > 97% (HPLC)
 Formula : C₉₅H₉₄N₄
 M.W. : 1291.79 g/mole
 UV : 378 nm (in CH₂Cl₂)
 PL : 426 nm (in CH₂Cl₂)



LT-N261 | MeOPBI

2-(2-Methoxyphenyl)-1,3-dimethyl-1H-benzoimidazol-3-ium iodide

Grade : > 99%
 Formula : C₁₆H₁₇IN₂O
 M.W. : 380.22 g/mole




LT-N262 | TNAP

2,2'-(Naphthalene-2,6-diylidene)dimalononitrile

CAS No. : 6251-01-0
 Grade : > 99%
 Formula : C₁₆H₆N₄
 M.W. : 254.25 g/mole
 TGA : > 150 °C (0.5% weight loss)

Reference : *Journal of Physical Chemistry C* (2014), 118(10), 5284-5293




LT-N2001 | Di-NPB

N⁺,N⁺-(Biphenyl-4,4'-diyl)bis(N⁺-(naphthalen-1-yl)-N⁺,N⁺-diphenylbiphenyl-4,4'-diamine)

CAS No. : 292827-46-4
 Grade : Sublimed, > 99% (HPLC)
 Formula : C₈₀H₅₈N₄
 M.W. : 1075.34 g/mole
 TGA : > 300 °C (0.5% weight loss)


Reference : *Adv. Funct. Mater.*2012, 22(2),405-414



LT-N2002 | 3DMFL-BPA

N⁺,N⁺-(9,9-Dimethyl-9H-fluorene-2,7-diyl)bis(9,9-dimethyl-N⁺,N⁺,N⁺-triphenyl-9H-fluorene-2,7-diamine)


CAS No. : 354987-71-6
 Grade : Sublimed, > 99% (HPLC)
 Formula : C₈₁H₆₆N₄
 M.W. : 1095.42 g/mole
 UV : 378 nm (in CH₂Cl₂)
 PL : 426 nm (in CH₂Cl₂)
 TGA : > 300 °C (0.5% weight loss)



LT-N2003 | NPB-DPA

N⁺,N⁺-(Biphenyl-4,4'-diyl)bis(N⁺-(naphthalen-1-yl)-N⁺,N⁺-diphenylbenzene-1,4-diamine)

CAS No. : 910058-11-6
 Grade : Sublimed, > 99% (HPLC)
 Formula : C₆₈H₅₀N₄
 M.W. : 923.15 g/mole
 UV : 311, 355 nm (in CH₂Cl₂)
 PL : 516 nm (in CH₂Cl₂)
 TGA : > 300 °C (0.5% weight loss)




Organic Light Emitting Diode (OLED)

Hole Injection Layer(HIL) Materials

LT-N2004 | β -NPB-DPA

*N*²,*N*^{2'}-(Biphenyl-4,4'-diyl)bis(*N*¹-(naphthalen-2-yl)-*N*⁴,*N*^{4'}-diphenylbenzene-1,4-diamine)


CAS No. : 1207378-72-0
Grade : Sublimed, > 99% (HPLC)
Formula : C₆₈H₅₀N₄
M.W. : 923.15 g/mole
UV : 311, 355 nm (in CH₂Cl₂)
PL : 516 nm (in CH₂Cl₂)
TGA : > 300 °C (0.5% weight loss)



LT-S973 | TCNQ

7,7,8,8-Tetracyanoquinodimethane

CAS No. : 1518-16-7
Grade : Sublimed, > 99%
Formula : C₁₂H₄N₄
M.W. : 204.19 g/mole
UV : 259, 404 nm (in CH₂Cl₂)
TGA : > 210 °C (0.5% weight loss)




Lumtec

LT-E107 | MCP


1,3-Bis(carbazol-9-yl)benzene

CAS No. : 550378-78-4
 Grade : Sublimed, > 99.5% (HPLC)
 Formula : $C_{30}H_{20}N_2$
 M.W. : 408.49 g/mole
 UV : 292, 338 nm (in THF)
 PL : 360 nm (in THF)
 TGA : > 250 °C (0.5% weight loss)

**LT-E108** | TCP


1,3,5-Tris(carbazol-9-yl)benzene

CAS No. : 148044-07-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{42}H_{27}N_3$
 M.W. : 573.68 g/mole
 UV : 292, 337 nm (in THF)
 PL : 358 nm (in THF)
 TGA : > 310 °C (0.5% weight loss)

**LT-E207** | TcTa


4,4',4''-Tris(carbazol-9-yl)triphenylamine

CAS No. : 139092-78-7
 Grade : Sublimed, > 99.5% (HPLC)
 Formula : $C_{54}H_{36}N_4$
 M.W. : 740.89 g/mole
 UV : 293, 326 nm (in THF)
 PL : 385 nm (in THF)
 TGA : > 410 °C (0.5% weight loss)
 Reference : *Physical Chemistry Chemical Physics* (2013),
 15(38), 15850-15855.

**LT-E409** | CBP


4,4'-Bis(carbazol-9-yl)biphenyl

CAS No. : 58328-31-7
 Grade : Sublimed, > 99.5% (HPLC)
 Formula : $C_{36}H_{24}N_2$
 M.W. : 484.59 g/mole
 UV : 292, 318 nm (in THF)
 PL : 369 nm (in THF)
 TGA : > 320 °C (0.5% weight loss)

**LT-E414** | CDBP


4,4'-Bis(carbazol-9-yl)-2,2'-dimethylbiphenyl

CAS No. : 604785-54-8
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{38}H_{28}N_2$
 M.W. : 512.64 g/mole
 UV : 292, 340 nm (in THF)
 PL : 349, 364 nm (in THF)
 TGA : > 280 °C (0.5% weight loss)

**LT-N415** | DMFL-CBP

2,7-Bis(carbazol-9-yl)-9,9-dimethylfluorene

CAS No. : 226958-06-1
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{39}H_{28}N_2$
 M.W. : 524.65 g/mole
 UV : 293, 341 nm (in THF)
 PL : 363 nm (in THF)
 TGA : > 330 °C (0.5% weight loss)




Organic Light Emitting Diode (OLED)

Phosphorescent Host Materials

LT-N416 | Spiro-CBP

2,2',7,7'-Tetrakis(carbazol-9-yl)-9,9-spirobifluorene


CAS No. : 214078-86-1
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{23}H_{44}N_4$
M.W. : 377.16 g/mole
UV : 292, 342 nm (in THF)
PL : 370 nm (in THF)
TGA : > 480 °C (0.5% weight loss)



LT-N418 | DPFL-CBP

2,7-Bis(carbazol-9-yl)-9,9-ditolylfluorene


CAS No. : 1174006-50-8
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{51}H_{36}N_2$
M.W. : 676.84 g/mole
UV : 293, 344 nm (in THF)
PL : 367 nm (in THF)
TGA : > 330 °C (0.5% weight loss)



LT-N419 | FL-2CBP

9,9-Bis[4-(carbazol-9-yl)-phenyl]fluorene


CAS No. : 1431945-64-0
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{49}H_{32}N_2$
M.W. : 648.79 g/mole
UV : 292, 340 nm (in THF)
PL : 364 nm (in THF)
TGA : > 370 °C (0.5% weight loss)



LT-N420 | Spiro-2CBP

2,7-Bis(carbazol-9-yl)-9,9-spirobifluorene

CAS No. : 924899-38-7
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{49}H_{36}N_2$
M.W. : 646.78 g/mole
UV : 293,343 nm (in THF)
PL : 367 nm (in THF)
TGA : > 360 °C (0.5% weight loss)




LT-N448 | UGH-2

1,4-Bis(triphenylsilyl)benzene

CAS No. : 40491-34-7
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{42}H_{34}Si_2$
M.W. : 594.89 g/mole
UV : 265 nm (in CH_2Cl_2)
PL : 296 nm (in CH_2Cl_2)
TGA : > 270 °C (0.5% weight loss)

Reference : 1. *Applied Physics Letters*, 86, 263502 (2005)
2. *Chem. Mater.* 2004, 16, 4743-4747




LT-N449 | UGH-3

1,3-Bis(triphenylsilyl)benzene

CAS No. : 18920-16-6
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{42}H_{34}Si_2$
M.W. : 594.89 g/mole
UV : 265 nm (in THF)
PL : 301, 418 nm (in THF)
TGA : > 270 °C (0.5% weight loss)

Reference : *Chem. Mater.* 2004, 16, 4743-4747




LT-N450 | MPMP

Bis(4-*N,N*-diethylamino-2-methylphenyl)-4-methylphenylmethane

CAS No. : 70895-80-6
 Grade : > 99% (HPLC)
 Formula : $C_{30}H_{40}N_2$
 M.W. : 428.65 g/mole
 UV : 272, 309 nm (in THF)
 PL : 349 nm (in THF)
 TGA : > 190 °C (0.5% weight loss)

Reference : 1. *Appl. Phys. Lett. Vol. 85, No. 21, 22 November 2004*
 2. *Appl. Phys. Lett. 87, 193501 (2005)*




LT-N451 | DOFL-CBP

2,7-Bis(carbazol-9-yl)-9,9-dioctylfluorene

CAS No. : 848900-30-1
 Grade : > 99% (HPLC)
 Formula : $C_{53}H_{56}N_2$
 M.W. : 721.03 g/mole
 UV : 292, 340 nm (in THF)
 PL : 362 nm (in THF)
 TGA : > 310 °C (0.5% weight loss)

Reference : *Chem. Mater. 2004, 16, 4743-4747*




LT-N482 | BST

4,4''-Di(triphenylsilyl)-*p*-terphenyl

CAS No. : 1046146-39-7
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{54}H_{42}Si_2$
 M.W. : 747.08 g/mole
 UV : 296 nm (in CH_2Cl_2)
 PL : 358 nm (in CH_2Cl_2)
 TGA : > 360 °C (0.5% weight loss)

Reference : *Adv. Funct. Mater. 2008, 18, 485*




LT-N483 | BSB

4,4'-Di(triphenylsilyl)-biphenyl

CAS No. : 18826-13-6
 Grade : Sublimed, > 99%
 Formula : $C_{48}H_{36}Si_2$
 M.W. : 670.99 g/mole
 UV : 271 nm (in CH_2Cl_2)
 PL : 432 nm (in CH_2Cl_2)
 TGA : > 320 °C (0.5% weight loss)

Reference : *Adv. Funct. Mater. 2008, 18, 485*




LT-N484 | CzSi

9-(4-*tert*-Butylphenyl)-3,6-bis(triphenylsilyl)-9*H*-carbazole

CAS No. : 898546-82-2
 Grade : Sublimed, > 99%
 Formula : $C_{59}H_{49}NSi_2$
 M.W. : 816.19 g/mole
 UV : 275,301 nm (in CH_2Cl_2)
 PL : 354 nm (in CH_2Cl_2)
 TGA : > 320 °C (0.5% weight loss)

Reference : *Adv. Mater. 2006, 18, 1216*




LT-N485 | CzC

9-(4-*tert*-Butylphenyl)-3,6-ditrityl-9*H*-carbazole

CAS No. : 956373-04-9
 Grade : Sublimed, > 99%
 Formula : $C_{60}H_{49}N$
 M.W. : 784.04 g/mole
 UV : 277,305 nm (in CH_2Cl_2)
 PL : 369 nm (in CH_2Cl_2)
 TGA : > 330 °C (0.5% weight loss)

Reference : *Appl. Mater. Interfaces, 2009, 1(3), 567-574*



Organic Light Emitting Diode (OLED)


Phosphorescent Host Materials

LT-N491 | 26DCzPPy

2,6-Bis(3-(9H-carbazol-9-yl)phenyl)pyridine

CAS No. : 1013405-24-7
Grade : Sublimed, > 99% (HPLC)
Formula : C₄₁H₂₇N₃
M.W. : 561.67 g/mole
UV : 239, 292 nm (in CH₂Cl₂)
PL : 410 nm (in CH₂Cl₂)
TGA : > 370 °C (0.5% weight loss)

Reference : Chem. Mater. 2008, 20, 1691-1693



LT-N493 | EFIN

9,9-Dimethyl-N,N-diphenyl-7-(4-(1-phenyl-1H-benzo[d]imidazol-2-yl)phenyl)-9H-fluorene-2-amine

CAS No. : 1705571-72-7
Grade : Sublimed, > 99% (HPLC)
Formula : C₄₆H₃₅N₃
M.W. : 629.79 g/mole
UV : 370 nm (in CH₂Cl₂)
PL : 428 nm (in CH₂Cl₂)
TGA : > 320 °C (0.5% weight loss)

Reference : Advanced Functional Materials (2009), 19, (16), 2661-2670




LT-N494 | 35DCzPPy

3,5-Bis(3-(9H-carbazol-9-yl)phenyl)pyridine

CAS No. : 1013405-25-8
Grade : Sublimed, > 99% (HPLC)
Formula : C₄₁H₂₇N₃
M.W. : 561.67 g/mole
UV : 307, 317 nm (in CH₂Cl₂)
PL : 347 nm (in CH₂Cl₂)
TGA : > 290 °C (0.5% weight loss)

Reference : Chem. Mater. 2008, 20, 1691-1693




LT-N496 | SPPO1

9,9-Spirobifluorene-2-yl-diphenyl-phosphine oxide

CAS No. : 1125547-88-7
Grade : Sublimed, > 99% (HPLC)
Formula : C₃₇H₂₅OP
M.W. : 516.57 g/mole
UV : 307, 317 nm (in CH₂Cl₂)
PL : 346 nm (in CH₂Cl₂)
TGA : > 290 °C (0.5% weight loss)

Reference : Appl. Phys. Lett. 94, 013301 2009




LT-N497 | SimCP

9,9'-(5-(Triphenylsilyl)-1,3-phenylene)bis(9H-carbazole)

CAS No. : 850221-63-5
Grade : Sublimed, > 99% (HPLC)
Formula : C₄₈H₃₄N₂Si
M.W. : 666.88 g/mole
UV : 293, 312, 345 nm (in THF)
PL : 446 nm (in THF)
TGA : > 300 °C (0.5% weight loss)

Reference : Adv. Mater., 17, 285, 2005




LT-N499 | FATPA

4,4,8,8,12,12-Hexa-p-tolyl-4H-8H-12H-12C-aza-dibenzo[cd,mn]pyrene

CAS No. : 1131007-94-7
Grade : Sublimed, > 99% (HPLC)
Formula : C₆₃H₅₁N
M.W. : 822.09 g/mole
UV : 311 nm (in Toluene)
PL : 375 nm (in Toluene)
TGA : > 320 °C (0.5% weight loss)

Reference : Org. Lett., Vol. 11, No. 7, 2009, 1503-1506




LT-N4006 | PPT

2,8-Bis(diphenylphosphoryl)dibenzo[*b,d*]thiophene

CAS No. : 1019842-99-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{36}H_{26}O_2P_2S$
 M.W. : 584.60 g/mole
 UV : 315, 328 nm (in CH_2Cl_2)
 PL : 351 nm (in CH_2Cl_2)
 TGA : > 320 °C (0.5% weight loss)

Reference : *J. Mater. Chem.*, 2011, 21, 14604–14609




LT-N4008 | UGH-1

Bis(2-methylphenyl)diphenylsilane

CAS No. : 18849-24-6
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{26}H_{24}Si$
 M.W. : 364.55 g/mole
 UV : 265 nm (in CH_2Cl_2)
 PL : 298 nm (in CH_2Cl_2)

Reference : *Chem. Mater.*, 2004, 16, 4743-4747




LT-N4009 | SimCP2

Bis[3,5-di(9*H*-carbazol-9-yl)phenyl]diphenylsilane

CAS No. : 944465-42-3
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{72}H_{48}N_4Si$
 M.W. : 977.26 g/mole
 UV : 324, 338 nm (in CH_2Cl_2)
 PL : 362 nm (in CH_2Cl_2)
 TGA : > 380 °C (0.5% weight loss)

Reference : *J. Mater. Chem.* 2010, 20, 8411-8416




LT-N4010 | TCz1

3,6-Bis(carbazol-9-yl)-9-(2-ethyl-hexyl)-9*H*-carbazole

CAS No. : 1021423-90-4
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{44}H_{39}N_3$
 M.W. : 609.8 g/mole
 UV : 293 nm (in CH_2Cl_2)
 PL : 396 nm (in CH_2Cl_2)
 TGA : > 280 °C (0.5% weight loss)

Reference : *Appl. Phys. Lett.*, 1996, 69, 093304, 2010




LT-N4011 | PPO21

3-(Diphenylphosphoryl)-9-(4-(diphenylphosphoryl)phenyl)-9*H*-carbazole

CAS No. : 1226860-68-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{42}H_{31}NO_2P_2$
 M.W. : 643.65 g/mole
 UV : 294, 338 nm (in CH_2Cl_2)
 PL : 361 nm (in THF)
 TGA : > 300 °C (0.5% weight loss)

Reference : *Adv. Mater.* 2010, 22, 1-5



Organic Light Emitting Diode (OLED)


Phosphorescent Host Materials

LT-N4012 | CzTP

3,6-Bis[(3,5-diphenyl)phenyl]-9-phenyl-carbazole

CAS No. : 1201649-79-7
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{54}H_{37}N$
M.W. : 699.88 g/mole
UV : 260 nm (in CH_2Cl_2)
PL : 390 nm (in CH_2Cl_2)
TGA : > 360 °C (0.5% weight loss)

Reference : *Chem. Commun.*, 2009, 6655-6657




LT-N4014 | ADBP

10-(4'-(Diphenylamino)biphenyl-4-yl)acridin-9(10H)-one

CAS No. : 1188546-10-2
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{37}H_{26}N_2O$
M.W. : 514.62 g/mole
UV : 375, 394 nm (in CH_2Cl_2)
PL : 408 nm (in CH_2Cl_2)
TGA : > 310 °C (0.5% weight loss)

Reference : *Org. Lett.*, Vol. 11, No. 19, 2009




LT-N4015 | SPPO13

2,7-Bis(diphenylphosphoryl)-9,9'-spirobifluorene

CAS No. : 1234510-13-4
Grade : > 99% (HPLC)
Formula : $C_{49}H_{34}O_2P_2$
M.W. : 716.74 g/mole
UV : 282 nm (in CH_2Cl_2)
PL : 373 nm (in CH_2Cl_2)
TGA : > 330 °C (0.5% weight loss)

Reference : *Thin Solid Films* 519 (2010) 906-910




LT-N4016 | DCB

1,4-Bis((9H-carbazol-9-yl)methyl)benzene

CAS No. : 166256-60-6
Grade : > 99% (HPLC)
Formula : $C_{32}H_{24}N_2$
M.W. : 436.55 g/mole
UV : 293 nm (in CH_2Cl_2)
PL : 351, 366 nm (in CH_2Cl_2)
TGA : > 230 °C (0.5% weight loss)

Reference : *Appl. Phys.* 41 (2008) 105114-105117




LT-N4017 | BCPO

Bis-4-(N-carbazolyl)phenyl)phenylphosphine oxide

CAS No. : 1233407-28-7
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{42}H_{29}N_2OP$
M.W. : 608.67 g/mole
UV : 292 nm (in CH_2Cl_2)
PL : 391 nm (in CH_2Cl_2)
TGA : > 360 °C (0.5% weight loss)

Reference : *Adv. Mater.* 2010, 22, 2468-2471




LT-N4018 | POAPF

2,7-Bis(diphenylphosphoryl)-9-(4-diphenylamino)phenyl-9'-phenyl-fluorene

CAS No. : 1198361-98-6
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{61}H_{45}NO_2P_2$
M.W. : 885.96 g/mole
UV : 293, 315 nm (in CH_2Cl_2)
PL : 383 nm (in CH_2Cl_2)
TGA : > 350 °C (0.5% weight loss)

Reference : *Advanced Functional Materials* (2009), 19, (17), 2834-2843




LT-N4025 | PPO27

2,7-Bis(diphenylphosphoryl)-9-phenyl-9H-carbazole

CAS No. : 1299463-56-1
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{22}H_{13}NO_2P_2$
 M.W. : 643.65 g/mole
 UV : 257, 309 nm (in CH_2Cl_2)
 PL : 386 nm (in CH_2Cl_2)
 TGA : > 350 °C (0.5% weight loss)

Reference : *J. Mater. Chem.*, 2011, 21, 5638-5644




LT-N4027 | PFN-DOF

Poly[(9,9-bis(3'-(N,N-dimethylamino)propyl)-2,7-fluorene)-alt-2,7-(9,9-dioctylfluorene)]

CAS No. : 673474-75-4
 Grade : $M_w > 10,000$ (GPC)
 Formula : $(C_{52}H_{70}N_2)_n$
 UV : 378 nm (in CH_2Cl_2)
 PL : 414 nm (in CH_2Cl_2)
 Solubility : Soluble in CH_2Cl_2 , $CHCl_3$, Toluene

Reference : *Chem. Mater.*, Vol. 16, No. 4, 2004




LT-N4029 | SPPO21

2,7-Bis(diphenylphosphoryl)spiro[fluorene-7,11'-benzofluorene]

CAS No. : 1270960-64-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{53}H_{36}O_2P_2$
 M.W. : 766.8 g/mole
 UV : 287 nm (in CH_2Cl_2)
 PL : 419 nm (in CH_2Cl_2)
 TGA : > 350 °C (0.5% weight loss)

Reference : *Thin Solid Films* 519 (2011) 4342-4346




LT-N4034 | Dspiro-PO

Di(9,9-spirobifluorene-2-yl)-phenyl-phosphine oxide

CAS No. : 824426-27-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{56}H_{35}OP$
 M.W. : 754.85 g/mole
 UV : 275 nm (film)
 PL : 365 nm (film)
 TGA : > 350 °C (0.5% weight loss)

Reference : *Appl. Phys. Lett.* 91, 103507(2007)




LT-N4035 | NP3PPO

4''',4''''-(Phenylphosphoryl)bis(N-1-naphthyl-N-phenyl-1,1':4',1''-terphenyl-4-amine)

CAS No. : 1415633-86-1
 Grade : > 98% (HPLC)
 Formula : $C_{74}H_{53}N_2OP$
 M.W. : 1017.20 g/mole
 UV : 349 nm (in CH_2Cl_2)
 PL : 466 nm (in CH_2Cl_2)
 TGA : > 320 °C (0.5% weight loss)

Reference : *Chem. Eur. J.* 2012, 18, 13828-13835




LT-N4036 | NP4PPO

4''',4''''-(Phenylphosphoryl)bis(N-1-naphthyl-N-phenyl-1,1':4',1''':4''-quaterphenyl-4-amine)

CAS No. : 1415633-87-2
 Grade : > 98% (HPLC)
 Formula : $C_{86}H_{61}N_2OP$
 M.W. : 1169.39 g/mole
 UV : 347 nm (in CH_2Cl_2)
 PL : 471 nm (in CH_2Cl_2)
 TGA : > 450 °C (0.5% weight loss)

Reference : *Chem. Eur. J.* 2012, 18, 13828-13835



Organic Light Emitting Diode (OLED)


Phosphorescent Host Materials

LT-N4037 | PCMO

Poly[3-(carbazol-9-ylmethyl)-3-methyloxetane]

Grade : $M_w > 10000$ (GPC)
Formula : $(C_{17}H_{17}NO)_n$
UV : 237, 263 nm (in CH_2Cl_2)
Solubility : Soluble in $CHCl_3$,
Chlorobenzene, Dichlorobenzene

Reference : *J. Mater. Chem.*, 2011, 21, 9546-9552




LT-N4039 | CzPO2

9-(3,5-Bis(diphenylphosphoryl)phenyl)-9H-carbazole

CAS No. : 1256573-07-5
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{42}H_{31}NO_2P_2$
M.W. : 643.65 g/mole
UV : 291 nm (in CH_2Cl_2)
PL : 426 nm (in CH_2Cl_2)
TGA : > 270 °C (0.5% weight loss)

Reference : *Org. Lett.*, 2011, 13, 3146-3149




LT-N4041 | G3-tCbz

6-(3',6'-Di-tert-butyl-6-(3,6-di-tert-butyl-9H-carbazol-9-yl)-9H-3,9'-bicarbazol-9-yl)-9-(4-(3',6'-di-tert-butyl-6-(3,6-di-tert-butyl-9H-carbazol-9-yl)-9H-3,9'-bicarbazol-9-yl)phenyl)-3',6'-bis(3,6-di-tert-butyl-9H-carbazol-9-yl)-9H-3,9'-bicarbazole

CAS No. : 1025079-68-8
Grade : > 98% (HPLC)
Formula : $C_{174}H_{172}N_{10}$
M.W. : 2403.29 g/mole
UV : 244, 349 nm (in CH_2Cl_2)
PL : 402 nm (in CH_2Cl_2)


Reference : *Adv. Mater.*, 2012, 24, 1873-1877



LT-N4042 | Ph-MCP

3,5-Di(9H-carbazol-9-yl)biphenyl

CAS No. : 750573-28-5
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{36}H_{24}N_2$
M.W. : 484.59 g/mole
UV : 241, 292 nm (in CH_2Cl_2)
PL : 363 nm (in CH_2Cl_2)
TGA : > 270 °C (0.5% weight loss)




LT-N4046 | CNBzIm

9-Phenyl-3,6-bis(4-(1-phenyl-1H-benzo[d]imidazol-2-yl)phenyl)-9H-carbazole

CAS No. : 1258780-50-5
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{56}H_{37}N_5$
 M.W. : 779.93 g/mole
 UV : 299 nm (in CH_2Cl_2)
 PL : 392 nm (in CH_2Cl_2)
 TGA : > 350 °C (0.5% weight loss)

Reference : *J. Mater. Chem.*, 2011, 21, 19249-19256




LT-N4047 | mCPPPO1

9-(3-(9H-Carbazol-9-yl)phenyl)-3-(diphenylphosphoryl)-9H-carbazole

CAS No. : 1296229-26-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{42}H_{29}N_2OP$
 M.W. : 608.67 g/mole
 UV : 324, 338 nm (in CH_2Cl_2)
 PL : 361 nm (in CH_2Cl_2)
 TGA : > 270 °C (0.5% weight loss)

Reference : 1. *Organic Electronics* 12 (2011) 1711-1715
 2. *Adv. Mater.* 2011, 23, 1436-1441




LT-N4048 | TSPPO1

Diphenyl-4-triphenylsilylphenyl-phosphine oxide

CAS No. : 1286708-86-8
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{36}H_{29}OPSi$
 M.W. : 536.67 g/mole
 UV : 266 nm (in CH_2Cl_2)
 PL : 298 nm (in CH_2Cl_2)
 TGA : > 300 °C (0.5% weight loss)

Reference : *Adv. Mater.* 2011, 23, 1436-1441




LT-N4049 | SPPO11

9,9-Spirobifluoren-4-yl-diphenyl-phosphineoxide

CAS No. : 1312423-72-5
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{37}H_{25}OP$
 M.W. : 516.57 g/mole
 UV : 273, 309, 323 nm (in CH_2Cl_2)
 PL : 346 nm (in CH_2Cl_2)
 TGA : > 250 °C (0.5% weight loss)

Reference : *Organic Electronics* 11 (2010) 1059-1065




LT-N4050 | DFCzPO

9-(8-(Diphenylphosphoryl)dibenzo[b,d]furan-2-yl)-9H-carbazole

CAS No. : 1349901-36-5
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{36}H_{24}NO_2P$
 M.W. : 533.56 g/mole
 UV : 291, 338 nm (in CH_2Cl_2)
 PL : 392 nm (in CH_2Cl_2)
 TGA : > 300 °C (0.5% weight loss)

Reference : *Chem. Asian J.* 2011, 6, 2895-2898




LT-N4051 | DBFPPO

Dibenzofuran-4-yl-diphenyl-phosphine-oxide

CAS No. : 1268162-33-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{24}H_{17}O_2P$
 M.W. : 368.36 g/mole
 UV : 288 nm (in CH_2Cl_2)
 PL : 328 nm (in CH_2Cl_2)
 TGA : > 320 °C (0.5% weight loss)

Reference : *Chem. Eur. J.* 2011, 17, 445-449



Organic Light Emitting Diode (OLED)


Phosphorescent Host Materials

LT-N4057 | PCz-BFP

3-(3-(9H-Carbazol-9-yl)phenyl)benzofuro[2,3-b]pyridine

CAS No. : 1424369-36-7
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{29}H_{18}N_2O$
M.W. : 410.47 g/mole
UV : 241, 293 nm (in CH_2Cl_2)
PL : 364 nm (in CH_2Cl_2)
TGA : > 270 °C (0.5% weight loss)

Reference : *Adv. Mater.* 2013, 25, 596-600




LT-N4058 | BTP1

3-(3-(9H-Carbazol-9-yl)phenyl)benzo[4,5]thieno[2,3-b]pyridine

CAS No. : 1421599-23-6
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{29}H_{18}N_2S$
M.W. : 426.53 g/mole
UV : 291, 339 nm (in CH_2Cl_2)
PL : 365 nm (in CH_2Cl_2)
TGA : > 270 °C (0.5% weight loss)

Reference : *Chem. Commun.*, 2013, 49, 1446-1448




LT-N4060 | DPEPO

Bis[2-(diphenylphosphino)phenyl]ether oxide

CAS No. : 808142-23-6
Grade : Sublimed, > 99.5%
Formula : $C_{36}H_{28}O_3P_2$
M.W. : 570.55 g/mole
UV : 388 nm (in CH_2Cl_2)
PL : 311 nm (in CH_2Cl_2)
TGA : > 320 °C (0.5% weight loss)

Reference : *Chem. Eur. J.* 2011, 17, 5800-5803




LT-N4062 | 2,7-F-PVF

Poly[9-sec-butyl-2,7-difluoro-9H-carbazole]

CAS No. : 1227083-33-1
Grade : $M_w > 30,000$ (GPC)
Formula : $(C_{14}H_9F_2N)_n$
UV : 261, 294 nm (in CH_2Cl_2)
PL : 397 nm (in CH_2Cl_2)
Solubility : Soluble in $CHCl_3$,
Chlorobenzene, Dichlorobenzene

Reference : *J Phys. Chem. C* 2012, 116, 20681-20687




LT-N4063 | DV-CBP

4,4'-Bis(3-((4-vinylphenoxy)methyl)-9H-carbazol-9-yl)biphenyl

CAS No. : 1428901-78-3
Grade : > 99% (HPLC)
Formula : $C_{54}H_{40}N_2O_2$
M.W. : 748.91 g/mole
UV : 246, 295 nm (in CH_2Cl_2)
PL : 381 nm (in CH_2Cl_2)

Reference : *Organic Electronics*, 14, 2013, 1614-1620




LT-N4069 | m-CBP

3,3'-Di(9H-carbazol-9-yl)biphenyl

CAS No. : 342638-54-4
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{26}H_{24}N_2$
 M.W. : 484.59 g/mole
 UV : 292, 328 nm (in CH_2Cl_2)
 PL : 349 nm (in THF)
 TGA : > 250 °C (0.5% weight loss)

Reference : 1. *Organic Electronics* 12 (2011) 1711-1715
 2. *Adv. Mater.* 2011, 23, 1436-1441




LT-N4070 | pBCb2Cz

9-(4-(9H-Pyrido[2,3-b]indol-9-yl)phenyl)-9H-3,9'-bicarbazole

CAS No. : 1446517-60-7
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{41}H_{26}N_4$
 M.W. : 574.67 g/mole
 UV : 239, 294 nm (in CH_2Cl_2)
 PL : 381 nm (in CH_2Cl_2)
 TGA : > 250 °C (0.5% weight loss)


Reference : 1. *Organic Electronics* 12 (2011) 1711-1715
 2. *Adv. Mater.* 2011, 23, 1436-1441



LT-N4072 | PYD-2Cz

2,6-Di(9H-carbazol-9-yl)pyridine


CAS No. : 168127-49-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{29}H_{19}N_3$
 M.W. : 409.48 g/mole
 UV : 241, 290 nm (in CH_2Cl_2)
 PL : 373 nm (in THF)
 TGA : > 250 °C (0.5% weight loss)



LT-N4077 | PVK

Poly(9-vinylcarbazole)


CAS No. : 25067-59-8
 Grade : $M_w > 20,000$ (GPC)
 Formula : $(C_{14}H_{11}N)_n$
 UV : 261, 294 nm (in CH_2Cl_2)
 PL : 380 nm (in THF)
 Solubility : Soluble in $CHCl_3$,
 Chlorobenzene, Dichlorobenzene



LT-N4078 | PVK

Poly(9-vinylcarbazole)


CAS No. : 25067-59-8
 Grade : $M_w > 100,000$ (GPC)
 Formula : $(C_{14}H_{11}N)_n$
 UV : 261, 294 nm (in CH_2Cl_2)
 PL : 380 nm (in THF)
 Solubility : Soluble in $CHCl_3$,
 Chlorobenzene, Dichlorobenzene



LT-N4079 | CPCBPTz

3-(4-(9H-Carbazol-9-yl)phenyl)-9-(4,6-diphenyl-1,3,5-triazin-2-yl)-9H-carbazole

CAS No. : 1407183-68-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{45}H_{29}N_5$
 M.W. : 639.75 g/mole
 UV : 252, 331 nm (in CH_2Cl_2)
 TGA : > 250 °C (0.5% weight loss)



Organic Light Emitting Diode (OLED)


Phosphorescent Host Materials

LT-N4080 | 46DCzPPM

4,6-Bis(3-(9H-carbazol-9-yl)phenyl)pyrimidine

CAS No. : 1262678-77-2
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{40}H_{26}N_4$
M.W. : 562.66 g/mole
UV : 240, 292 nm (in CH_2Cl_2)
PL : 476 nm (in CH_2Cl_2)
TGA : > 280 °C (0.5% weight loss)

Reference : *Organic Electronics* (2011), 12(5), 843-850




LT-N4081 | STDBT-4

3'-(Dibenzo[b,d]thiophen-4-yl)-10-phenyl-10H-spiro[acridine-9,9'-fluorene]

CAS No. : 1467099-24-6
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{43}H_{27}NS$
M.W. : 589.75 g/mole
UV : 316 nm (in Toluene)
PL : 376 nm (in Toluene)
TGA : > 270 °C (0.5% weight loss)


Reference : *Journal of Materials Chemistry C: Materials for Optical and Electronic Devices* (2013), 1(40), 6575-6584



LT-N4082 | DTP-mCP

9-(3,5-Di(triphenylen-2-yl)phenyl)-9H-carbazole


CAS No. : 1498411-20-3
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{54}H_{33}N$
M.W. : 695.85 g/mole
UV : 273 nm (in $CHCl_3$)
PL : 377 nm (in $CHCl_3$)
TGA : > 280 °C (0.5% weight loss)



LT-N4085 | BCzPh

9,9'-Diphenyl-9H,9'H-3,3'-bicarbazole

CAS No. : 571102-62-2
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{36}H_{24}N_2$
M.W. : 484.59 g/mole
UV : 303 nm (in CH_2Cl_2)
TGA : > 250 °C (0.5% weight loss)




LT-N4086 | CBBPE

9,9'-(Oxybis([1,1'-biphenyl]-4',3'-diyl))bis(9H-carbazole)

CAS No. : 1470161-29-5
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{48}H_{32}N_2O$
M.W. : 652.78 g/mole
UV : 240 nm (in CH_2Cl_2)
PL : 350 nm (in CH_2Cl_2)
TGA : > 270 °C (0.5% weight loss)

Reference : *Dyes and Pigments* (2013), 98(3), 372-376




LT-N4088 | BCzSCN

9,9'-Diphenyl-9H,9'H-3,3'-bicarbazole-6-carbonitrile

CAS No. : 1462896-48-5
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{37}H_{23}N_3$
M.W. : 509.6 g/mole
UV : 250, 301 nm (in CH_2Cl_2)
PL : 416 nm (in CH_2Cl_2)
TGA : > 270 °C (0.5% weight loss)


Reference : *Journal of Materials Chemistry C: Materials for Optical and Electronic Devices* (2013), 1(48), 8177-8185



LT-N4092 | CbBPCb

3,3'-Di(9H-pyrido[2,3-b]indol-9-yl)biphenyl

Formula : $C_{34}H_{22}N_4$
M.W. : 486.57 g/mole




LT-N4099 | m-cbtz

9-(3-(3,5-Di(pyridin-2-yl)-1H-1,2,4-triazol-1-yl)phenyl)-9H-carbazole

CAS No. : 1361953-33-4
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{30}H_{20}N_6$
M.W. : 464.52 g/mole
UV : 293, 340 nm (in THF)
PL : 427 nm (in THF)
TGA : > 270 °C (0.5% weight loss)

Reference : *Journal of Materials Chemistry* (2012), 22(12), 5410-5418




LT-N4100 | BBICT

4-(4,6-Bis[12-phenylindolo[2,3-a]carbazol-11(12H)-yl]-1,3,5-triazin-2-yl)-benzonitrile

CAS No. : 1617496-77-1
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{58}H_{34}N_8$
M.W. : 842.94 g/mole
UV : 260, 330 nm (in CH_2Cl_2)
PL : 450 nm (in CH_2Cl_2)
TGA : > 320 °C (0.5% weight loss)

Reference : *Advanced Functional Materials* (2014), 24(23), 3551-3561




LT-N4101 | POBPM DPA

2'-(Diphenylphosphinyl)-N,N-bis(4-methylphenyl)-1,1'-biphenyl]-2-amine

CAS No. : 1579983-04-2
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{38}H_{32}NOP$
M.W. : 549.64 g/mole
UV : 444 nm (in Toluene)
PL : 458 nm (in 2-MeTHF)
TGA : > 250 °C (0.5% weight loss)

Reference : *Angew. Chem. Int. Ed.* 2014, 53, 2147-2151




LT-N4102 | BCzTPA

4,4'-(9H,9'H-3,3'-Bicarbazole- 9,9'-diyl)bis(N,N-diphenylaniline)

CAS No. : 1032174-52-9
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{60}H_{42}N_4$
M.W. : 819.00 g/mole
UV : 310, 341 nm (film)
PL : 397 nm (film)

Reference : 1. *Adv. Funct. Mater.* 2013, 23, 5550-5555 ;
2. *Adv. Mater.* 2012, 24, 3212-3217
3. *J. Mater. Chem. C*, 2015, 3, 1700




LT-N4107 | POCz3

3,3',3''-Phosphinylidynetris[9-phenyl-9H-carbazole

CAS No. : 1392204-91-9
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{54}H_{36}N_3OP$
M.W. : 773.86 g/mole
UV : 260 nm (in CH_2Cl_2)
PL : 351 nm (in CH_2Cl_2)
TGA : > 300 °C (0.5% weight loss)

Reference : 1. *Dalton Transactions* (2015), 44(33), 14613-14624

2. *Organic Electronics* (2011), 12(12), 2025-2032




Organic Light Emitting Diode (OLED)

Phosphorescent Host Materials

LT-N4115 | BPOPB

1,3-Bis(3-(diphenylphosphoryl)phenyl)benzene

Grade : Sublimed, > 99% (HPLC)
Formula : $C_{42}H_{32}O_2P_2$
M.W. : 630.65 g/mole
UV : 251, 290 nm (in CH_2Cl_2)
PL : 340 nm (in CH_2Cl_2)
TGA : > 270 °C (0.5% weight loss)




LT-N4116 | CzPPQ

9-(4-(4-Phenylquinolin-2-yl)phenyl)-9H-carbazole

CAS No. : 1617494-49-1
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{33}H_{22}N_2$
M.W. : 446.54 g/mole
UV : 247, 292, 342 nm (in CH_2Cl_2)
PL : 442 nm (in CH_2Cl_2)
TGA : > 270 °C (0.5% weight loss)


Reference : 1. *Journal of Materials Chemistry C: Materials for Optical and Electronic Devices*, 2(30), 6183-6191; 2014
2. *ACS Applied Materials & Interfaces* (2015), 7(19), 10466-10474



LT-N4129 | o-CBP

2,2'-Di(9H-carbazol-9-yl)biphenyl


CAS No. : 592551-54-7
Grade : Sublimed, > 99%
Formula : $C_{36}H_{24}N_2$
M.W. : 484.59 g/mole



LT-N4147 | NCzmPy2Cz

9-(6-(5H-pyrrolo[2,3-b:4,5-b']dipyridin-5-yl)pyridin-2-yl)-9'-phenyl-9H,9'-H-3,3'-bicarbazole


CAS No. : 2041519-51-9
Grade : Sublimed, >99 % (HPLC)
Formula : $C_{45}H_{28}N_6$
M.W. : 652.74 g/mole
UV : 300,329 nm (in CH_2Cl_2)
PL : 385,402 nm (in CH_2Cl_2)
HOMO : -5.54 eV
LUMO : -2.16 eV



LT-N4148 | mCPCN

9-(3-(9H-carbazol-9-yl)phenyl)-9H-carbazole-3-carbonitrile


CAS No. : 1392506-99-8
Grade : Sublimed, >99% (HPLC)
Formula : $C_{31}H_{19}N_3$
M.W. : 433.5 g/mole



LT-N4150 | TCzCN

9-(3''-(carbazol-9-yl)-[1,1',3',1''-terphenyl]-3-yl)-carbazole-3-carbonitrile

Grade : Sublimed, >99% (HPLC)
Formula : $C_{43}H_{27}N_3$
M.W. : 585.69 g/mole




LT-N4159 | m-POPpyCz

(5-(9'-H-[9,3':6',9''-tercarbazol]-9'-yl)pyridin-3-yl) diphenylphosphine


CAS No. : 2151067-61-5
Grade : Sublimed, >99 % (HPLC)
Formula : $C_{53}H_{35}N_4OP$
M.W. : 774.84 g/mole
UV : 296,326,343(film)
Emission : 423 nm (film)
HOMO : -5.63 eV
LUMO : -2.54 eV

Reference : *ACS Appl. Mater. Interfaces* 2017, 9, 37888-37897



LT-N4160 | PFN-B

Formula : $(C_{29}H_{34}N_2)_n$



LT-N798 | PXZ-DCPP

7,10-bis(phenoxazine)-2,3-dicyanopyrazino phenanthrene

CAS No. : 1803288-00-7
Grade : Sublimed, >99 % (HPLC)
Formula : $C_{42}H_{22}N_6O_2$
M.W. : 642.66 g/mole
UV : 323, 372 nm (in Toluene)
PL : 533 nm (in Toluene)
HOMO : -5.19 eV
LUMO : -3.52 eV
Triplet Energy : 0.09 eV


Reference : *Organic Electronics* 59 (2018) 32-38

Lumtec

LT-E401 | Alq3

Tris(8-hydroxy-quinolino)aluminium

CAS No. : 2085-33-8
 Grade : Sublimed, > 99.5% (HPLC)
 Formula : $C_{27}H_{18}AlN_3O_3$
 M.W. : 459.43 g/mole
 UV : 259 nm (in THF)
 PL : 512 nm (in THF)
 TGA : > 270 °C (0.5% weight loss)

**LT-E403** | ADN


9,10-Di(naphth-2-yl)anthracene

CAS No. : 122648-99-1
 Grade : Sublimed, > 99.5% (HPLC)
 Formula : $C_{34}H_{22}$
 M.W. : 430.54 g/mole
 UV : 375, 395 nm (in THF)
 PL : 425 nm (in THF)
 TGA : > 290 °C (0.5% weight loss)

**LT-E404** | TBADN


2-tert-Butyl-9,10-di(naphth-2-yl)anthracene

CAS No. : 274905-73-6
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{38}H_{30}$
 M.W. : 486.64 g/mole
 UV : 375, 395 nm (in THF)
 PL : 431 nm (in THF)
 TGA : > 290 °C (0.5% weight loss)

**LT-E405** | DPVBi


4,4'-Bis(2,2-diphenylethenyl)-1,1'-biphenyl

CAS No. : 142289-08-5
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{40}H_{30}$
 M.W. : 510.23 g/mole
 UV : 353 nm (in $CHCl_3$)
 PL : 442 nm (in $CHCl_3$)
 TGA : > 300 °C (0.5% weight loss)

**LT-E406** | p-DMDPVBi


4,4'-bis(2,2-dip-tolylvinyl)biphenyl Chemical

CAS No. : 135804-06-7
 Grade : > 99% (HPLC)
 Formula : $C_{44}H_{38}$
 M.W. : 566.77 g/mole

**LT-E408** | TDAF

2,7-Bis[9,9-di(4-methylphenyl)-fluoren-2-yl]-9,9-di(4-methylphenyl)fluorene


CAS No. : 474918-42-8
 Grade : Sublimed, > 98% (HPLC)
 Formula : $C_{81}H_{62}$
 M.W. : 1035.36 g/mole
 UV : 353 nm (in THF)
 PL : 419 nm (in THF)
 TGA : > 370 °C (0.5% weight loss)

Reference : *J. Phys. Chem. C* 2007, 111, 108-115

LT-E410 | MADN

2-Methyl-9,10-bis(naphthalen-2-yl)anthracene

CAS No. : 804560-00-7
 Grade : Sublimed, > 99.5% (HPLC)
 Formula : $C_{35}H_{24}$
 M.W. : 444.57 g/mole
 UV : 379, 399 nm (in CH_2Cl_2)
 PL : 439 nm (in CH_2Cl_2)
 TGA : > 300 °C (0.5% weight loss)

**LT-E411** | BSBF


2-(9,9-Spirobifluoren-2-yl)-9,9-spirobifluorene

CAS No. : 664345-18-0
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{50}H_{30}$
 M.W. : 630.77 g/mole
 UV : 330 nm (in THF)
 PL : 384 nm (in THF)
 TGA : > 310 °C (0.5% weight loss)

Reference : *Org. Lett., Vol. 7, No. 23, 2005***LT-E412** | TSBF


2,7-Bis(9,9-spirobifluoren-2-yl)-9,9-spirobifluorene

CAS No. : 518997-91-6
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{75}H_{44}$
 M.W. : 945.15 g/mole
 UV : 350 nm (in THF)
 PL : 415 nm (in THF)
 TGA : > 390 °C (0.5% weight loss)

Reference : *J. Phys. Chem. C 2007, 111, 108-115***LT-E413** | BDAF

2-[9,9-Di(4-methylphenyl)-fluoren-2-yl]-9,9-di(4-methylphenyl)fluorene

CAS No. : 854046-47-2
 Grade : Sublimed, > 97% (HPLC)
 Formula : $C_{54}H_{42}$
 M.W. : 690.91 g/mole
 UV : 333 nm (in THF)
 PL : 386 nm (in THF)
 TGA : > 310 °C (0.5% weight loss)

Reference : *Org. Lett., Vol. 7, No. 23, 2005***LT-N428** | 2,2'-Spiro-Pye


2,2'-Dipyrenyl-9,9-spirobifluorene

CAS No. : 831222-16-3
 Grade : Sublimed, > 98% (HPLC)
 Formula : $C_{57}H_{32}$
 M.W. : 716.86 g/mole
 UV : 279, 347 nm (in THF)
 PL : 414 nm (in THF)
 TGA : > 440 °C (0.5% weight loss)

**LT-N429** | TSB3

1,3,5-Tri(pyren-1-yl)benzene


CAS No. : 349666-25-7
 Grade : Sublimed, > 95% (HPLC)
 Formula : $C_{54}H_{30}$
 M.W. : 678.81 g/mole
 UV : 280, 352 nm (in THF)
 PL : 388 nm (in THF)
 TGA : > 360 °C (0.5% weight loss)

Reference : *Synthetic Metals 143 (2004) 89-96*

LT-N447 | BPPF


9,9-Bis[4-(pyrenyl)phenyl]-9H-fluorene

CAS No. : 1174006-47-3
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{57}H_{34}$
 M.W. : 718.88 g/mole
 UV : 280, 344 nm (in THF)
 PL : 402 nm (in THF)
 TGA : > 430 °C (0.5% weight loss)

**LT-N452** | TPBA

2,2'-Bi(9,10-diphenyl-anthracene)

CAS No. : 172285-72-2
 Grade : Sublimed, > 99%
 Formula : $C_{52}H_{34}$
 M.W. : 658.83 g/mole
 UV : 294, 333 nm (in THF)
 PL : 455 nm (in THF)
 TGA : > 390 °C (0.5% weight loss)

Reference: *Appl. Phys. Lett.*, 89, 063504(2006).**LT-N458** | Spiro-Pye


2,7-Dipyrenyl-9,9-spirobifluorene

CAS No. : 886456-80-0
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{57}H_{32}$
 M.W. : 716.86 g/mole
 UV : 363 nm (in THF)
 PL : 424 nm (in THF)
 TGA : > 440 °C (0.5% weight loss)

**LT-N472** | p-Bpye


1,4-Di(pyren-1-yl)benzene

CAS No. : 475460-77-6
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{38}H_{22}$
 M.W. : 478.58 g/mole
 UV : 280, 351 nm (in CH_2Cl_2)
 PL : 431 nm (in CH_2Cl_2)
 TGA : > 320 °C (0.5% weight loss)

Reference: *Advanced Functional Materials* (2008), 18, (1), 67-75.**LT-N473** | m-Bpye


1,3-Di(pyren-1-yl)benzene

CAS No. : 1616657-81-8
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{38}H_{22}$
 M.W. : 478.58 g/mole
 UV : 279, 350 nm (in THF)
 PL : 384 nm (in THF)
 TGA : > 330 °C (0.5% weight loss)

**LT-N478** | DBPenta

6,13-Di-biphenyl-4-yl-pentacene

CAS No. : 1254039-84-3
 Grade : Sublimed, > 99%
 Formula : $C_{46}H_{30}$
 M.W. : 582.73 g/mole
 UV : 305 nm (in THF)
 PL : 620 nm (in THF)
 TGA : > 360 °C (0.5% weight loss)


Reference: *J. Phys. Chem. Lett.* 2012, 3, 1079-1083

LT-N479 | DNP

3,9-Di(naphthalen-2-yl)perylene and 3,10-di(naphthalen-2-yl) perylene mixture

CAS No. : 959611-30-4 and 919089-75-1
 Grade : Sublimed, > 99%
 Formula : $C_{40}H_{24}$
 M.W. : 504.62 g/mole
 UV : 434, 460 nm (in THF)
 PL : 488 nm (in THF)
 TGA : > 320 °C (0.5% weight loss)

Reference : *Journal of Applied Physics*, 102,104908(2007)




LT-N481 | DMPPP

1,1'-(2,5-Dimethyl-1,4-phenylene)dipyrene

CAS No. : 1036404-84-8
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{40}H_{26}$
 M.W. : 506.63 g/mole
 PL : 397 nm (in CH_2Cl_2)
 TGA : > 350 °C (0.5% weight loss)

Reference : *Adv. Mater.* 2012, 24, 5867-5871




LT-N487 | TPyPA

Tris[4-(pyrenyl)-phenyl]amine

CAS No. : 349669-77-8
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{66}H_{39}N$
 M.W. : 846.02 g/mole
 UV : 271 nm (in CH_2Cl_2)
 PL : 479 nm (in CH_2Cl_2)
 TGA : > 470 °C (0.5% weight loss)

Reference : *Appl. Phys. Lett.*, 91, 023503 (2007).




LT-N488 | BANE

10,10'-Di(biphenyl-4-yl)-9,9'-bianthracene

CAS No. : 172285-79-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{52}H_{34}$
 M.W. : 658.83 g/mole
 UV : 260 nm (in CH_2Cl_2)
 PL : 449 nm (in CH_2Cl_2)
 TGA : > 320 °C (0.5% weight loss)

Reference : *Organic Electronics* 8 (2007), 735-742.




LT-N489 | 4P-NPB

N,N'-Di-(1-naphthalenyl)-*N,N'*-diphenyl-[1,1':4',1'':4'',1'''-4''''-quaterphenyl]-4,4''''-diamine

CAS No. : 948552-24-7
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{56}H_{40}N_2$
 M.W. : 740.93 g/mole
 UV : 351 nm (in CH_2Cl_2)
 PL : 422 nm (in CH_2Cl_2)
 TGA : > 380 °C (0.5% weight loss)

Reference : *Adv. Mater.* 2007, 19, 3672-3676




LT-N490 | BUBH-3

4,4'-Di[10-(naphthalen-1-yl)anthracen-9-yl]biphenyl

CAS No. : 1002328-32-6
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{60}H_{38}$
 M.W. : 758.94 g/mole
 UV : 262 nm (in CH_2Cl_2)
 PL : 420 nm (in CH_2Cl_2)
 TGA : > 440 °C (0.5% weight loss)

Reference : *Appl. Phys. Lett.* 91, 183504 (2007)




LT-N4004 | BAnFPye

1-(7-(9,9'-Bianthracen-10-yl)-9,9-dimethyl-9H-fluoren-2-yl)pyrene

CAS No. : 1705571-70-5
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{59}H_{38}$
 M.W. : 746.93 g/mole
 UV : 356 nm (in CH_2Cl_2)
 PL : 433 nm (in CH_2Cl_2)
 TGA : > 440 °C (0.5% weight loss)


Reference : TW. 1402243

**LT-N4005** | DAnF6Pye

1-(7-(9,9'-Bianthracen-10-yl)-9,9-dihexyl-9H-fluoren-2-yl)pyrene

CAS No. : 1705571-71-6
 Grade : > 99% (HPLC)
 Formula : $C_{69}H_{58}$
 M.W. : 877.20 g/mole
 UV : 358 nm (in CH_2Cl_2)
 PL : 437 nm (in CH_2Cl_2)


Reference : TW. 1402243

**LT-N4040** | BAnF8Pye

1-(7-(9,9'-Bianthracen-10-yl)-9,9-dioctyl-9H-fluoren-2-yl)pyrene

CAS No. : 1258522-34-7
 Grade : > 99% (HPLC)
 Formula : $C_{73}H_{66}$
 M.W. : 943.31 g/mole
 UV : 257, 356 nm (in CH_2Cl_2)
 PL : 440 nm (in CH_2Cl_2)
 TGA : > 330 °C (0.5% weight loss)


Reference : TW. 1402243

**LT-N4084** | ADP

9,10-Diphenylanthracene


CAS No. : 1499-10-1
 Grade : Sublimed, > 99%
 Formula : $C_{26}H_{18}$
 M.W. : 330.42 g/mole
 TGA : > 150 °C (0.5% weight loss)

Reference : Journal of Chemical Education (2013), 90(6), 786-789

**LT-N4087** | SBFF2B

1,4-Di(spiro[benzo[c]fluorene-7,9'-fluorene]-5-yl)benzene


CAS No. : 1499-10-1
 Grade : Sublimed, > 99%
 Formula : $C_{26}H_{18}$
 M.W. : 330.42 g/mole

**LT-N4091** | 6FAlq3

Tris(6-fluoro-8-hydroxy-quinolato)aluminium

CAS No. : 1257308-66-9
 Grade : > 99% (NMR)
 Formula : $C_{27}H_{15}AlF_3N_3O_3$
 M.W. : 513.4 g/mole
 UV : 375 nm (in CH_2Cl_2)
 PL : 495 nm (in CH_2Cl_2)
 TGA : > 220 °C (0.5% weight loss)

Reference : Chemistry - A European Journal (2011), 17(33), 9076-9082




LT-N4093 | Znq2

Bis(8-hydroxyquinoline) zinc

CAS No. : 13978-85-3
 Formula : $C_{18}H_{12}N_2O_2Zn$
 M.W. : 353.71 g/mole
 PL : 465 nm (film)
 TGA : > 220 °C (0.5% weight loss)

Reference : *Organic Electronics* (2008), 9(5), 625-634




LT-N4094 | CPPyC

9-(5-(3-(9H-Carbazol-9-yl)phenyl)pyridin-3-yl)-9H-carbazole

CAS No. : 1583238-16-7
 Grade : > 99% (HPLC)
 Formula : $C_{35}H_{23}N_3$
 M.W. : 485.58 g/mole
 TGA : > 200 °C (0.5% weight loss)

Reference : *Chemistry of Materials* (2014), 26(7), 2368-2373




LT-N4096 | SF3PO

Bis(9,9-spirobifluorene-3-yl)-phenylphosphane oxide

CAS No. : 1454615-69-0
 Grade : > 99% (HPLC)
 Formula : $C_{37}H_{25}OP$
 M.W. : 516.57 g/mole
 UV : 308, 314 nm (in CH_2Cl_2)
 PL : 322 nm (in CH_2Cl_2)
 TGA : > 200 °C (0.5% weight loss)


Reference : *Organic Electronics* (2013), 14(7), 1924-1930



LT-N4108 | POSTF

2'-(diphenylphosphoryl)-10-phenyl-10H-spiro[acridine-9,9'-fluorene]


Formula : $C_{43}H_{30}NOP$
 M.W. : 607.68 g/mole



LT-N4110 | SSTF

10-Phenyl-2'-(triphenylsilyl)-10H-spiro[acridine-9,9'-fluorene]


CAS No. : 1454372-37-2
 Formula : $C_{49}H_{35}NSi$
 M.W. : 665.89 g/mole



LT-N4113 | 4ICDPy

Indolo[3,2-a]carbazole, 5,12-dihydro-6,7-dimethyl-5,12-di-4-pyridinyl

CAS No. : 1803246-66-3
 Formula : $C_{30}H_{22}N_4$
 M.W. : 438.52 g/mole



Organic Light Emitting Diode (OLED)

Fluorescent Host Materials


LT-N4114 | 3CzPPF

3-[3-(9H-carbazol-9-yl)phenyl]furo[2,3-b:5,4-b']dipyridine

CAS No. : 1443793-91-6

Formula : $C_{28}H_{17}N_3O$

M.W. : 411.45 g/mole




LT-N4122 | BCz-Si

9-Phenyl-9'-(triphenylsilyl)-9H,9'H-3,3'-bicarbazole

CAS No. : 1770916-57-8

Formula : $C_{48}H_{34}N_2Si$

M.W. : 666.88 g/mole



LT-N4126 | DPTPCz


3-(4,6-Diphenyl-1,3,5-triazin-2-yl)-9-phenyl-9H-carbazole

CAS No. : 1313391-57-9

Grade : Sublimed, > 99% (HPLC)

Formula : $C_{33}H_{22}N_4$

M.W. : 706.75 g/mole



LT-N4127 | POPH


(5-Terphenyl-1,3-phenylene)bis(diphenylphosphine oxide)

CAS No. : 1818448-28-0

Grade : Sublimed, > 99% (HPLC)

Formula : $C_{48}H_{36}O_2P_2$

M.W. : 706.75 g/mole



LT-N4128 | TCPZ


2,4,6-Tris(3-(9H-carbazol-9-yl)phenyl)-1,3,5-triazine

CAS No. : 890148-68-2

Grade : Sublimed, > 99%

Formula : $C_{57}H_{36}N_6$

M.W. : 804.94 g/mole



LT-N4129 | o-CBP


2,2'-Di(9H-carbazol-9-yl)biphenyl

CAS No. : 592551-54-7

Grade : Sublimed, > 99%

Formula : $C_{36}H_{24}N_2$

M.W. : 484.59 g/mole



LT-N4151 | MAD-1N


2-Methyl-9,10-di(naphthalen-1-yl)anthracene

CAS No. : 863497-34-1

Grade : Sublimed, >99% (HPLC)

Formula : $C_{35}H_{24}$


M.W. : 444.57 g/mole



LT-N4152 | SF34

Synthesis of 3-(9,9'-spirofluorenyl-4-yl)-9,9'-spirofluorene


CAS No. : 1799329-54-6
Grade : Sublimed, >99% (HPLC)
Formula : $C_{50}H_{30}$
M.W. : 630.77 g/mole



LT-N4154 | pDPFB

1,4-bis(9-phenyl-9H-fluoren-9-yl)benzene


CAS No. : 1138331-98-2
Grade : Sublimed, >99%
Formula : $C_{44}H_{30}$
M.W. : 558.71 g/mole



LT-N4156 |

9-(naphthalen-1-yl)-10-(naphthalen-2-yl)anthracene

CAS No. : 855828-36-3
Grade : Sublimed, >99% (HPLC)
Formula : $C_{34}H_{22}$
M.W. : 430.54 g/mole




Lumtec


LT-E501 | Coumarin 6

3-(2-Benzothiazolyl)-7-(diethylamino)coumarin


CAS No.	: 38215-36-0
Grade	: Sublimed, > 99% (HPLC)
Formula	: C ₂₀ H ₁₈ N ₂ O ₂ S
M.W.	: 350.43 g/mole
UV	: 443 nm (in THF)
PL	: 493 nm (in THF)
TGA	: > 260 °C (0.5% weight loss)

**LT-E502** | C545T2,3,6,7-Tetrahydro-1,1,7,7-tetramethyl-1*H*,5*H*,11*H*-10-(2-benzothiazolyl)quinolizino[9,9*a*,1*gh*]coumarin


CAS No.	: 155306-71-1
Grade	: Sublimed, > 99% (HPLC)
Formula	: C ₂₆ H ₂₆ N ₂ O ₂ S
M.W.	: 430.56 g/mole
UV	: 473 nm (in THF)
PL	: 506 nm (in THF)
TGA	: > 240 °C (0.5% weight loss)

**LT-E503** | DMQA*N,N'*-Dimethyl-quinacridone

CAS No.	: 19205-19-7
Grade	: Sublimed, > 99% (HPLC)
Formula	: C ₂₂ H ₁₆ N ₂ O ₂
M.W.	: 340.37 g/mole
UV	: 294, 510 nm (in THF)
PL	: 523 nm (in THF)
TGA	: > 300 °C (0.5% weight loss)


**LT-E504** | *fac*-Ir(ppy)₃*fac*-Tris(2-phenylpyridine)iridium(III)

CAS No.	: 94928-86-6
Grade	: Sublimed, > 99% (HPLC)
Formula	: C ₃₃ H ₂₄ IrN ₃
M.W.	: 654.78 g/mole
UV	: 282, 377 nm (in THF)
PL	: 513 nm (in THF)
TGA	: > 300 °C (0.5% weight loss)


**LT-E505** | Ir(ppy)₂(acac)

Bis(2-phenylpyridine)(acetylacetonate)iridium(III)

CAS No.	: 337526-85-9
Grade	: Sublimed, > 99% (HPLC)
Formula	: C ₂₇ H ₂₃ IrN ₂ O ₂
M.W.	: 599.70 g/mole
UV	: 259 nm (in THF)
PL	: 524 nm (in THF)
TGA	: > 270 °C (0.5% weight loss)

**LT-N506** | Ir(mppy)₃Tris[2-(*p*-tolyl)pyridine]iridium(III)

CAS No.	: 149005-33-4
Grade	: Sublimed, > 99% (HPLC)
Formula	: C ₃₆ H ₃₀ IrN ₃
M.W.	: 696.86 g/mole
UV	: 287, 373 nm (in CH ₂ Cl ₂)
PL	: 514 nm (in CH ₂ Cl ₂)
TGA	: > 330 °C (0.5% weight loss)


Reference: *Appl. Phys. Lett.*, Vol. 84, No. 14, 5 April 2004, 2476~2478.

LT-N507 | TTPA

9,10-Bis[*N,N*-di-(*p*-tolyl)-amino]anthracene

CAS No. : 177799-16-5
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{42}H_{36}N_2$
 M.W. : 568.75 g/mole
 UV : 294, 471 nm (in CH_2Cl_2)
 PL : 554 nm (in CH_2Cl_2)
 TGA : > 280 °C (0.5% weight loss)

Reference : *Chem. Mater.*, 2002, 14, 3958~3963.




LT-N508 | TPA

9,10-Bis[phenyl(*m*-tolyl)-amino]anthracene

CAS No. : 189263-81-8
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{40}H_{32}N_2$
 M.W. : 540.70 g/mole
 UV : 292, 458 nm (in CH_2Cl_2)
 PL : 532 nm (in CH_2Cl_2)
 TGA : > 270 °C (0.5% weight loss)

Reference : *Chem. Mater.*, 2002, 14, 3958~3963.




LT-N509 | Zn(BTZ)₂

Bis[2-(2-hydroxyphenyl)benzothiazolato]zinc(II)

CAS No. : 58280-31-2
 Grade : Sublimed, > 99%
 Formula : $C_{26}H_{16}N_2O_2S_2Zn$
 M.W. : 517.96 g/mole
 UV : 287, 334 nm (in CH_2Cl_2)
 PL : 458 nm (in CH_2Cl_2)
 TGA : > 300 °C (0.5% weight loss)


Reference : *Current Applied Physics*, 2 (2002), 295~298.



LT-N510 | BA-TTB

*N*¹⁰,*N*¹⁰,*N*^{10'},*N*^{10'}-Tetra-tolyl-9,9'-bianthracene-10,10'-diamine

CAS No. : 223735-62-4
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{56}H_{44}N_2$
 M.W. : 744.96 g/mole
 UV : 257 nm (in CH_2Cl_2)
 PL : 546 nm (in CH_2Cl_2)
 TGA : > 350 °C (0.5% weight loss)



LT-N511 | BA-TAD

*N*¹⁰,*N*¹⁰,*N*^{10'},*N*^{10'}-Tetraphenyl-9,9'-bianthracene-10,10'-diamine


CAS No. : 220721-68-6
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{52}H_{36}N_2$
 M.W. : 688.86 g/mole
 UV : 257 nm (in CH_2Cl_2)
 PL : 518 nm (in CH_2Cl_2)
 TGA : > 300 °C (0.5% weight loss)



LT-N512 | BA-NPB


*N*¹⁰,*N*^{10'}-Diphenyl-*N*¹⁰,*N*^{10'}-dinaphthalenyl-9,9'-bianthracene-10,10'-diamine

CAS No. : 885502-26-1
 Grade : Sublimed, > 95% (HPLC)
 Formula : $C_{60}H_{40}N_2$
 M.W. : 788.97 g/mole
 UV : 357, 441 nm (in CH_2Cl_2)
 PL : 517 nm (in CH_2Cl_2)
 TGA : > 340 °C (0.5% weight loss)




LT-N522 | TEG*fac*-Tris(2-(3-*p*-xylyl)phenyl)pyridine iridium(III)

CAS No. : 1338784-40-9
 Grade : > 99% (HPLC)
 Formula : $C_{57}H_{48}IrN_3$
 M.W. : 967.3 g/mole
 UV : 400 nm (in film)
 PL : 539 nm (in film)
 TGA : > 250 °C (0.5% weight loss)


Reference : *Appl. Phys. Lett.* 91, 103507(2007)**LT-N528** | 2PXZ-OXD2,5-Bis(4-(10*H*-phenoxazin-10-yl)phenyl)-1,3,4-oxadiazole

CAS No. : 1447998-13-1
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{38}H_{24}N_4O_3$
 M.W. : 584.62 g/mole
 UV : 291 nm (in Toluene)
 PL : 501.5 nm (in Toluene)
 TGA : > 270 °C (0.5% weight loss)


Reference : *Journal of Materials Chemistry C: Materials for Optical and Electronic Devices* (2013), 1(30), 4599-4604**LT-N529** | Ir(npy)₂acac

Bis(2-(naphthalen-2-yl)pyridine)(acetylacetonate) iridium(III)

CAS No. : 878393-09-0
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{35}H_{27}IrN_2O_2$
 M.W. : 699.82 g/mole
 TGA : > 270 °C (0.5% weight loss)


Reference : *Appl. Phys. Lett.* 91, 103507(2007)**LT-N548** | TmCzTrz9,9',9''-(5-(4,6-diphenyl-1,3,5-triazin-2-yl)benzene-1,2,3-triyl)tris(3,6-dimethyl-9*H*-carbazole)

CAS No. : 1808158-41-9
 Formula : $C_{63}H_{48}N_6$
 M.W. : 889.1 g/mole

**LT-N562** | Ir(dmppy-pro)2tmd


Bis(2-(3,5-dimethylphenyl)-4-propylpyridine)(2,2,6,6-tetramethylheptane-3,5-diketonate)iridium(III)

CAS No. : 2050041-60-4
 Grade : Sublimed, >99 % (HPLC)
 Formula : $C_{43}H_{55}IrN_2O_2$
 M.W. : 824.14 g/mole
 UV : 263,373,441 nm (in CHCl₃)

**LT-N564** | BPTAPA

N10,N10'-bis(4-isopropylphenyl)-N10,N10'-dip-tolyl-9,9'-bianthracene-10,10'-diamine


CAS No. : 1848973-32-9
 Grade : Sublimed, >99% (HPLC)
 Formula : $C_{60}H_{52}N_2$
 M.W. : 801.07 g/mole



LT-N5002 | Ir(3mppy)₃

Tris(2-phenyl-3-methyl-pyridine)iridium

CAS No. : 639006-72-7
Grade : Sublimed, > 99% (HPLC)
Formula : C₃₆H₃₀IrN₃
M.W. : 696.86 g/mole
UV : 283, 383 nm (in CH₂Cl₂)
PL : 522 nm (in CH₂Cl₂)
TGA : > 280 °C (0.5% weight loss)




Organic Light Emitting Diode (OLED)

Blue Dopant Materials

LT-E601 | BCzVBi

4,4'-Bis(9-ethyl-3-carbazovinylylene)-1,1'-biphenyl


CAS No. : 475480-90-1
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{44}H_{36}N_2$
M.W. : 592.77 g/mole
UV : 384 nm (in THF)
PL : 438 nm (in THF)
TGA : > 340 °C (0.5% weight loss)



LT-E602 | Perylene

Perylene


CAS No. : 198-55-0
Grade : Sublimed, > 99.5% (HPLC)
Formula : $C_{20}H_{12}$
M.W. : 252.31 g/mole
UV : 410, 436 nm (in THF)
PL : 471 nm (in THF)
TGA : > 200 °C (0.5% weight loss)



LT-E603 | TBPe

2,5,8,11-Tetra-*tert*-butylperylene


CAS No. : 80663-92-9
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{36}H_{44}$
M.W. : 476.73 g/mole
UV : 412, 438 nm (in THF)
PL : 487 nm (in THF)
TGA : > 220 °C (0.5% weight loss)



LT-E604 | BCzVB

1,4-Bis[2-(3-*N*-ethylcarbazoryl)vinyl]benzene


CAS No. : 62608-15-5
Grade : > 99% (HPLC)
Formula : $C_{38}H_{32}N_2$
M.W. : 516.67 g/mole
UV : 372, 388 nm (in $CHCl_3$)
PL : 441, 462 nm (in $CHCl_3$)
TGA : > 360 °C (0.5% weight loss)



LT-E605 | DPAVBi

4,4'-Bis[4-(*p*-tolylamino)styryl]biphenyl


CAS No. : 119586-44-6
Grade : > 99% (HPLC)
Formula : $C_{56}H_{48}N_2$
M.W. : 748.99 g/mole
UV : 405 nm (in THF)
PL : 475 nm (in THF)
TGA : > 320 °C (0.5% weight loss)



LT-E606 | DPAVB

4-(*Di-p*-tolylamino)-4'-[(*di-p*-tolylamino)styryl]stilbene


CAS No. : 596103-58-1
Grade : > 99% (HPLC)
Formula : $C_{50}H_{44}N_2$
M.W. : 672.90 g/mole
UV : 415 nm (in Toluene)
PL : 467, 496 nm (in Toluene)
TGA : > 340 °C (0.5% weight loss)



LT-E608 | BDAVBi

4,4'-Bis[4-(diphenylamino)styryl]biphenyl


CAS No. : 523977-57-3
 Grade : > 99% (HPLC)
 Formula : $C_{22}H_{20}N_2$
 M.W. : 692.89 g/mole
 UV : 399 nm (in THF)
 PL : 466 nm (in THF)
 TGA : > 360 °C (0.5% weight loss)



LT-N446 | Spiro-BDAVBi

2,7-Bis[4-(diphenylamino)styryl]-9,9-spirobifluorene


CAS No. : 436798-89-9
 Grade : > 99% (HPLC)
 Formula : $C_{65}H_{46}N_2$
 M.W. : 855.07 g/mole
 UV : 414 nm (in CH_2Cl_2)
 PL : 482 nm (in CH_2Cl_2)
 TGA : > 390 °C (0.5% weight loss)



LT-N623 | BNP3FL

N,N'-Bis(naphthalen-2-yl)-*N,N'*-bis(phenyl)-tris-(9,9-dimethylfluorenylene)


CAS No. : 669016-17-5
 Grade : > 99% (HPLC)
 Formula : $C_{77}H_{60}N_2$
 M.W. : 1013.31 g/mole
 UV : 387 nm (in THF)
 PL : 437 nm (in THF)
 TGA : > 450 °C (0.5% weight loss)



LT-N624 | MDP3FL

2,7-Bis[2-(phenyl(*m*-tolyl)amino)-9,9-dimethyl-fluorene-7-yl]-9,9-dimethyl-fluorene


CAS No. : 239476-24-5
 Grade : > 99% (HPLC)
 Formula : $C_{71}H_{60}N_2$
 M.W. : 941.25 g/mole
 UV : 385 nm (in CH_2Cl_2)
 PL : 460 nm (in CH_2Cl_2)
 TGA : > 430 °C (0.5% weight loss)



LT-N627 | N-BDAVBi

N-(4-((*E*)-2-(6-((*E*)-4-(Diphenylamino)styryl)naphthalen-2-yl)vinyl)phenyl)-*N*-phenylbenzenamine

CAS No. : 1032556-63-0
 Grade : > 99% (HPLC)
 Formula : $C_{50}H_{38}N_2$
 M.W. : 666.85 g/mole
 UV : 407 nm (in THF)
 PL : 469 nm (in THF)
 TGA : > 370 °C (0.5% weight loss)




LT-N629 | *fac*-Ir(Pmb)₃

fac-Iridium(III) tris(1-phenyl-3-methylbenzimidazolin-2-ylidene-*C,C'*)

CAS No. : 1542678-40-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{52}H_{33}IrN_6$
 M.W. : 813.96 g/mole
 UV : 299 nm (in THF)
 PL : 405 nm (in THF)
 TGA : > 330 °C (0.5% weight loss)

Reference : *Applied Physics Letters*. 87, 243507, 2005.




LT-N630 | *mer*-Ir(Pmb)₃

mer-Iridium(III) tris(1-phenyl-3-methylbenzimidazolin-2-ylidene-*C,C'*)

CAS No. : 926292-95-7
 Grade : > 99% (HPLC)
 Formula : C₄₂H₃₃IrN₆
 M.W. : 813.96 g/mole
 UV : 303 nm (in THF)
 PL : 415 nm (in THF)
 TGA : > 280 °C (0.5% weight loss)


Reference : *Applied Physics Letters*, 87, 243507, 2005.



LT-N631 | DSA-Ph

1-4-Di-[4-(*N,N*-diphenylamino)styryl]-benzene


CAS No. : 358374-59-1
 Grade : > 99% (HPLC)
 Formula : C₄₆H₃₆N₂
 M.W. : 616.79 g/mole
 UV : 409 nm (in Toluene)
 PL : 459, 487 nm (in Toluene)
 TGA : > 320 °C (0.5% weight loss)



LT-N632 | BCzSB

1,4-Bis(4-(9*H*-carbazol-9-yl)styryl)benzene

CAS No. : 320575-30-2
 Grade : > 99%
 Formula : C₄₆H₃₂N₂
 M.W. : 612.76 g/mole
 UV : 375 nm (in Toluene)
 PL : 427, 451 nm (in Toluene)
 TGA : > 310 °C (0.5% weight loss)




LT-N634 | Bepp₂

Bis(2-(2-hydroxyphenyl)-pyridine)beryllium

CAS No. : 220694-90-6
 Grade : Sublimed, > 99%
 Formula : C₂₂H₁₆BeN₂O₂
 M.W. : 349.39 g/mole
 PL : 445 nm (in CHCl₃)
 TGA : > 250 °C (0.5% weight loss)

Reference : 1. *Chem. Mater.*, 2000, 12 (9), pp 2672-2675
 2. *J. Mater. Chem.*, 2011, 21, 3551




LT-N635 | FlrN4

Bis(2,4-difluorophenylpyridinato)(5-(pyridin-2-yl)-1*H*-tetrazolate) iridium(III)

CAS No. : 1219078-44-0
 Grade : > 99% (HPLC)
 Formula : C₂₈H₁₆F₄IrN₇
 M.W. : 718.67 g/mole
 UV : 368 nm (in THF)
 PL : 459 nm (in THF)
 TGA : > 270 °C (0.5% weight loss)

Reference : *Adv. Mater.*, 17, 285, 2005




LT-N642 | MQAB

(*Z*)-6-Mesityl-*N*-(6-mesitylquinolin-2(1*H*)-ylidene)quinolin-2-amine-BF₂ complex

CAS No. : 1338788-44-5
 Grade : > 99% (HPLC)
 Formula : C₃₆H₃₂BF₂N₃
 M.W. : 555.47 g/mole
 UV : 338 nm (in CH₂Cl₂)
 PL : 476 nm (in CH₂Cl₂)
 TGA : > 280 °C (0.5% weight loss)

Reference : *Organic Electronics* 12(2011) 666-676




LT-N645 | DPAFVF

9-[4-(2-(7-(*N,N*-Diphenylamino)-9,9-diethylfluorene-2-yl)vinyl)phenyl]-9-phenyl-fluorene

CAS No. : 1239588-65-8
 Grade : > 99% (HPLC)
 Formula : C₅₆H₄₅N
 M.W. : 731.96 g/mole
 UV : 386 nm (in CH₂Cl₂)
 PL : 465 nm (in CH₂Cl₂)
 TGA : > 260 °C (0.5% weight loss)


Reference : *Synthetic Metals* 160 (2010) 1259-1265



LT-N646 | *mer*-Ir(pmi)₃

mer-Tris(1-phenyl-3-methylimidazolin-2-ylidene-*C,C*(2') iridium(III))


CAS No. : 870009-65-7
 Grade : > 99% (HPLC)
 Formula : C₃₀H₂₇IrN₆
 M.W. : 663.85 g/mole
 UV : 267 nm (in CH₂Cl₂)
 PL : 410 nm (in CH₂Cl₂)
 TGA : > 250 °C (0.5% weight loss)



LT-N658 | *fac*-Ir(dpbc)₃

fac-Tris(1,3-diphenyl-benzimidazolin-2-ylidene-*C,C*(2') iridium(III))

CAS No. : 888725-36-8
 Grade : > 99% (HPLC)
 Formula : C₅₇H₄₂IrN₆
 M.W. : 1003.2 g/mole
 UV : 281, 302 nm (in CH₂Cl₂)
 PL : 472 nm (in CH₂Cl₂)
 TGA : > 350 °C (0.5% weight loss)




LT-N662 | PCAN

9-(9-Phenylcarbazole-3-yl)-10-(naphthalene-1-yl)anthracene

CAS No. : 1261580-75-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : C₄₂H₂₇N
 M.W. : 545.67 g/mole
 UV : 244, 397 nm (in CH₂Cl₂)
 PL : 441 nm (in CH₂Cl₂)
 TGA : > 330 °C (0.5% weight loss)

Reference : *J. Mater. Chem.*, 2012, 22, 123-129




LT-N663 | N-DBAVBi-C6

4,4'-(1*E*,1'*E*)-2,2'-(Naphthalene-2,6-diyl)bis(ethene-2,1-diyl)bis(*N,N*-bis(4-hexylphenyl)aniline)

CAS No. : 1258522-36-9
 Grade : > 99% (HPLC)
 Formula : C₇₄H₆₆N₂
 M.W. : 1003.49 g/mole
 UV : 407 nm (in THF)
 PL : 469 nm (in THF)

Reference : *Organic Electronics* (2009), 10, (8), 1610-1614




LT-N669 | FK306

Bis[4-*tert*-butyl-2',6'-difluoro-2,3'-bipyridine](acetylacetonate)iridium(III)

CAS No. : 1421058-47-0
 Grade : > 99% (HPLC)
 Formula : C₃₃H₃₃F₄IrN₂O₂
 M.W. : 785.85 g/mole
 UV : 244 nm (in CH₂Cl₂)
 PL : 454 nm (in CH₂Cl₂)
 TGA : > 280 °C (0.5% weight loss)


Reference : *J. Mater. Chem. C*, 2013, 1, 1070-1075



LT-S9058 | BSB4


4,4'-Bis(4-(9H-carbazol-9-yl)styryl)biphenyl

CAS No.	: 850594-34-2
Grade	: Sublimed, > 99%
Formula	: C ₂₂ H ₁₆ N ₂
M.W.	: 688.86 g/mole
UV	: 367 nm (in THF)
PL	: 424, 444 nm (in THF)
TGA	: > 320 °C (0.5% weight loss)


**LT-N675** | 2PXZ-TAZ

10,10'-(4,4'-(4-Phenyl-4H-1,2,4-triazole-3,5-diyl)bis(4,1-phenylene))bis(10H-phenoxazine)

CAS No.	: 1447998-15-3
Grade	: Sublimed, > 99% (HPLC)
Formula	: C ₄₄ H ₂₉ N ₅ O ₂
M.W.	: 659.73 g/mole
UV	: 473 nm (in Toluene)
PL	: 462 nm
ΔEST	: 0.86 eV
TGA	: > 300 °C (0.5% weight loss)


Reference: *J. Mater. Chem. C*, 2013, 1,4599**LT-N677** | TPA-SBFFN²,N⁵,N⁸,N⁹-tetraphenylspiro[benzo[c]fluorene-7,9'-fluorene]-5,9-diamine

CAS No.	: 1262333-45-8
Grade	: Sublimed, > 99% (HPLC)
Formula	: C ₅₃ H ₃₆ N ₂
M.W.	: 700.87 g/mole

**LT-N678** | Ban-(3,5)-CF3


10,10'-Bis(3,5-bis(trifluoromethyl)phenyl)-9,9'-bianthracene

CAS No.	: 1505456-00-7
Grade	: > 99% (HPLC)
Formula	: C ₄₄ H ₂₂ F ₁₂
M.W.	: 778.63 g/mole
UV	: 259, 400 nm (in CH ₂ Cl ₂)
PL	: 440 nm (in CH ₂ Cl ₂)
TGA	: > 270 °C (0.5% weight loss)


Reference: *Journal of Materials Chemistry C: Materials for Optical and Electronic Devices* (2013), 1(48), 8117-8127**LT-N679** | Ir(tfpd)₂pic

Bis(3,4,5-trifluoro-2-(2-pyridyl)phenyl)-(2-carboxypyridyl)iridium(III)

CAS No.	: 1417790-60-3
Grade	: > 99% (HPLC)
Formula	: C ₂₈ H ₁₄ F ₆ IrN ₃ O ₂
M.W.	: 730.64 g/mole
UV	: 254 nm (in CH ₂ Cl ₂)
PL	: 483 nm (in CH ₂ Cl ₂)
TGA	: > 280 °C (0.5% weight loss)

Reference: *Dyes and Pigments* (2013), 96(1), 237-241**LT-N680** | BD-6MDPAN²,N⁵-Diphenyl-N⁸,N⁹-di-m-tolylspiro[benzo[c]fluorene-7,9'-fluorene]-5,9-diamine


CAS No.	: 1262281-91-3
Grade	: > 99% (HPLC)
Formula	: C ₅₅ H ₄₀ N ₂
M.W.	: 728.92 g/mole
UV	: 408 nm (in CH ₂ Cl ₂)
PL	: 468 nm (in CH ₂ Cl ₂)
TGA	: > 220 °C (0.5% weight loss)



LT-N681 | ACRSA

10-Phenyl-10*H*,10'*H*-spiro[acridine-9,9'-anthracen]-10'-one


CAS No. : 1206626-95-0
 Formula : C₃₂H₂₁NO
 M.W. : 435.52 g/mole



LT-N697 | Ir(Fppy)₃

Tris(2-(4,6-difluorophenyl)pyridine)iridium(III)


CAS No. : 387859-70-3
 Grade : > 99% (HPLC)
 Formula : C₃₃H₁₈F₆IrN₃
 M.W. : 762.72 g/mole
 UV : 262 nm (in CH₂Cl₂)
 PL : 493 nm (in CH₂Cl₂)
 TGA : > 250 °C (0.5% weight loss)



LT-N699 | DMAC-TRZ

10-(4-(4,6-diphenyl-1,3,5-triazin-2-yl)phenyl)-9,9-dimethyl-9,10-dihydroacridine


CAS No. : 1628752-98-6
 Formula : C₃₆H₂₈N₄
 M.W. : 516.63 g/mole



LT-N6004 | PtON7

2-(3-(3-methyl-2,3-dihydro-1*H*-imidazol-1-yl)phenoxy)-9-(pyridin-2-yl)-9*H*-carbazoleplatinum(II)


CAS No. : 1448175-22-1
 Grade : > 99%
 Formula : C₂₇H₁₉N₄OPt
 M.W. : 610.12 g/mole



LT-N6015 | DPASP

(E)-N,N-diphenyl-4-(4-(pyren-1-yl)styryl)aniline

CAS No. : 2005434-89-7
 Grade : > 99% (HPLC)
 Formula : C₄₂H₂₉N
 M.W. : 547.69 g/mole



Organic Light Emitting Diode (OLED)


Red Dopant Materials

LT-E701 | DCM

(E)-2-(2-(4-(Dimethylamino)styryl)-6-methyl-4H-pyran-4-ylidene)malononitrile

CAS No. : 51325-91-8
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{19}H_{17}N_3O$
M.W. : 303.36 g/mole
UV : 462 nm (in THF)
PL : 577 nm (in THF)
TGA : > 250 °C (0.5% weight loss)

Reference : *Appl. Phys. Lett.* 79, 7, P1045-1047, 2001.




LT-E702 | DCM2

4-(Dicyanomethylene)-2-methyl-6-julolidyl-9-enyl-4H-pyran

CAS No. : 51325-95-2
Grade : > 99% (HPLC)
Formula : $C_{23}H_{21}N_3O$
M.W. : 355.43 g/mole
UV : 497 nm (in THF)
PL : 605 nm (in THF)
TGA : > 230 °C (0.5% weight loss)

Reference : *Chem. Phys. Lett.* 287, 3~4, 455-460, 1998.




LT-E703 | DCJT

4-(Dicyanomethylene)-2-methyl-6-(1,1,7,7-tetramethyljulolidyl-9-enyl)-4H-pyran

CAS No. : 159788-00-8
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{27}H_{29}N_3O$
M.W. : 411.54 g/mole
UV : 497 nm (in THF)
PL : 604 nm (in THF)
TGA : > 270 °C (0.5% weight loss)


Reference : *Proc. 2nd Internat. Sym. Chem. Functional Dyes*, 1992, 536.



LT-E704 | DCJTb

4-(Dicyanomethylene)-2-tert-butyl-6-(1,1,7,7-tetramethyljulolidin-4-yl-vinyl)-4H-pyran


CAS No. : 200052-70-6
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{30}H_{35}N_3O$
M.W. : 453.62 g/mole
UV : 501 nm (in THF)
PL : 602 nm (in THF)
TGA : > 250 °C (0.5% weight loss)



LT-E706 | Eu(dbm)₃(Phen)

Tris(dibenzoylmethane)phenanthroline europium(III)


CAS No. : 17904-83-5
Grade : Sublimed, > 99%
Formula : $C_{57}H_{41}N_2O_6Eu$
M.W. : 1001.93 g/mole
UV : 257, 355 nm (in THF)
PL : 615 nm (in THF)
TGA : > 180 °C (0.5% weight loss)



LT-E707 | Rubrene

5,6,11,12-Tetraphenylnaphthacene


CAS No. : 517-51-1
Grade : Sublimed, > 99%
Formula : $C_{42}H_{28}$
M.W. : 532.67 g/mole
UV : 299 nm (in THF)
PL : 553 nm (in THF)
TGA : > 250 °C (0.5% weight loss)



LT-E709 | Ir(btp)₂(acac)

Bis(2-benzo[*b*]thiophen-2-yl-pyridine)(acetylacetonate)iridium(III)


CAS No.	: 343978-79-0
Grade	: Sublimed, > 99% (HPLC)
Formula	: C ₃₁ H ₂₃ IrN ₂ O ₂ S ₂
M.W.	: 711.87 g/mole
UV	: 283 nm (in THF)
PL	: 615 nm (in THF)
TGA	: > 310 °C (0.5% weight loss)



LT-N721 | Ir(fliq)₂(acac)

Bis[1-(9,9-dimethyl-9H-fluoren-2-yl)-isoquinoline](acetylacetonate)iridium(III)


CAS No.	: 1617506-77-0
Grade	: Sublimed, > 98.5% (HPLC)
Formula	: C ₅₃ H ₄₃ IrN ₂ O ₂
M.W.	: 932.14 g/mole
UV	: 285, 368 nm (in THF)
PL	: 653 nm (in THF)
TGA	: > 350 °C (0.5% weight loss)



LT-N724 | Ir(flq)₂(acac)

Bis[2-(9,9-dimethyl-9H-fluoren-2-yl)quinoline](acetylacetonate)iridium(III)

CAS No.	: 889750-25-8
Grade	: Sublimed, > 99% (HPLC)
Formula	: C ₅₃ H ₄₃ IrN ₂ O ₂
M.W.	: 932.14 g/mole
UV	: 309, 368 nm (in THF)
PL	: 615 nm (in THF)
TGA	: > 320 °C (0.5% weight loss)




LT-N727 | Ru(dtb-bpy)₃ · 2(PF₆)

Tris[4,4'-di-*tert*-butyl-(2,2')-bipyridine]ruthenium(III) complex

Grade	: Sublimed, > 99%
Formula	: C ₅₄ H ₇₂ F ₁₂ N ₆ P ₂ Ru
M.W.	: 1196.19 g/mole
UV	: 289, 462 nm (in THF)
PL	: 614 nm (in THF)
TGA	: > 350 °C (0.5% weight loss)

Reference : *Appl. Phys. Lett.* 79, 7, P1045-1047, 2001.




LT-N732 | TBRb

2,8-Di-*tert*-butyl-5,11-bis(4-*tert*-butylphenyl)-6,12-diphenyltetracene

CAS No.	: 682806-51-5
Grade	: Sublimed, > 99%
Formula	: C ₅₈ H ₆₀
UV	: 306 nm (in CH ₂ Cl ₂)
PL	: 571 nm (in CH ₂ Cl ₂)
TGA	: > 310 °C (0.5% weight loss)

Reference : *Thin Solid Films* 496 (2006) 626~630




LT-N733 | Ir(BT)₂(acac)

Bis(2-phenylbenzothiazolato)(acetylacetonate)iridium(III)

CAS No.	: 337526-88-2
Grade	: Sublimed, > 98.5% (HPLC)
Formula	: C ₃₁ H ₂₃ IrN ₂ O ₂ S ₂
M.W.	: 711.87 g/mole
UV	: 271 nm (in THF)
PL	: 563 nm (in THF)
TGA	: > 270 °C (0.5% weight loss)

Reference : *Journal of Organometallic Chemistry, Vol 689, Issue 26, P4882-4888, 2004.*




LT-N734 | Pt(TPBP)

Platinum(II) 5,10,15,20-tetraphenyltetrabenzoporphyrim

CAS No.	: 166174-05-6
Grade	: > 96% (HPLC)
Formula	: $C_{60}H_{36}N_4Pt$
M.W.	: 1008.03 g/mole
UV	: 430, 610 nm (in THF)
PL	: 765 nm (in THF)
TGA	: > 320 °C (0.5% weight loss)


Reference : *Angew. Chem. Int. Ed.* 2007, 46, 1109–1112



LT-N740 | Hex-Ir(phq)₂(acac)

Bis[2-(4-*n*-hexylphenyl)quinoline](acetylacetonate) iridium(III)

CAS No.	: 1404197-18-7
Grade	: 99% (HPLC)
Formula	: $C_{47}H_{51}IrN_2O_2$
M.W.	: 868.14 g/mole
UV	: 344 nm (in CH_2Cl_2)
PL	: 588 nm (in CH_2Cl_2)
TGA	: > 210 °C (0.5% weight loss)




LT-N741 | Hex-Ir(phq)₃

Tris[2-(4-*n*-hexylphenyl)quinoline]iridium(III)

CAS No.	: 1268460-37-2
Grade	: > 99% (HPLC)
Formula	: $C_{63}H_{66}IrN_3$
M.W.	: 1057.43 g/mole
UV	: 323 nm (in CH_2Cl_2)
PL	: 583 nm (in CH_2Cl_2)
TGA	: > 250 °C (0.5% weight loss)

Reference : *Synthetic Metals* 161 (2011) 148–152




LT-N742 | Ir(Mphq)₃

Tris[2-phenyl-4-methylquinoline]iridium(III)

CAS No.	: 1433853-90-7
Grade	: Sublimed, > 99% (HPLC)
Formula	: $C_{48}H_{36}IrN_3$
M.W.	: 847.04 g/mole
UV	: 259, 270 nm (in CH_2Cl_2)
PL	: 573 nm (in CH_2Cl_2)
TGA	: > 350 °C (0.5% weight loss)


Reference : *Journal of Information Display* Vol. 12, No. 1, March 2011, 51–55



LT-N743 | Ir(phq)₂tpy

Bis[2-phenylquinoline](2-(3-methylphenyl)pyridinate) iridium(III)

Grade	: Sublimed, > 99% (HPLC)
Formula	: $C_{42}H_{30}IrN_3$
M.W.	: 768.93 g/mole
UV	: 256, 271 nm (in CH_2Cl_2)
PL	: 604 nm (in CH_2Cl_2)
TGA	: > 320 °C (0.5% weight loss)




LT-N744 | Ir(fbi)₂(acac)

Bis[2-(9,9-diethyl-fluoren-2-yl)-1-phenyl-1*H*-benzo[*d*]imidazolato](acetylacetonate)iridium(III)

CAS No.	: 725251-24-1
Grade	: > 99% (HPLC)
Formula	: $C_{65}H_{57}IrN_4O_2$
M.W.	: 1118.40 g/mole
UV	: 421 nm (in THF)
PL	: 538 nm (in THF)
TGA	: > 270 °C (0.5% weight loss)

Reference : 1. *Angew. Chem. Int. Ed.* 2008, 47, 581
2. *Chem. Mater.* 2004, 16, 2480




LT-N745 | *fac*-Ir(ppy)₂Pc

Bis(2-phenylpyridine)(3-(pyridin-2-yl)-2H-chromen-2-one)iridium(III)

CAS No. : 1003562-42-2
 Grade : Sublimed, > 99% (HPLC)
 Formula : C₃₆H₂₄IrN₃O₂
 M.W. : 722.82 g/mole
 UV : 319 nm (in CH₂Cl₂)
 PL : 550 nm (in CH₂Cl₂)
 TGA : > 340 °C (0.5% weight loss)

Reference : *Thin Solid Films* 496 (2006) 626~630




LT-N746 | Ir(dpm)PQ₂

Bis(2-phenylquinoline)(2,2,6,6-tetramethylheptane-3,5-dionate)iridium(III)

CAS No. : 713079-03-9
 Grade : Sublimed, > 99% (HPLC)
 Formula : C₄₁H₃₉IrN₂O₂
 M.W. : 783.98 g/mole
 UV : 333 nm (in CH₂Cl₂)
 PL : 595 nm (in CH₂Cl₂)
 TGA : > 290 °C (0.5% weight loss)


Reference : *J. Photopolym. Sci. Technol.*, Vol.21, No.2, 2008



LT-N747 | Ir(dpm)(piq)₂

Bis(phenylisoquinoline)(2,2,6,6-tetramethylheptane-3,5-dionate) iridium(III)


CAS No. : 1202867-58-0
 Grade : Sublimed, > 99% (HPLC)
 Formula : C₄₁H₃₉IrN₂O₂
 M.W. : 783.98 g/mole
 UV : 354, 479 nm (in CH₂Cl₂)
 PL : 628 nm (in CH₂Cl₂)
 TGA : > 310 °C (0.5% weight loss)



LT-N748 | Ir(dpm)(piq)₂

Bis(phenylisoquinoline)(2,2,6,6-tetramethylheptane-3,5-dionate) iridium(III)

CAS No. : 1258323-36-2
 Grade : Sublimed, > 99% (HPLC)
 Formula : C₄₁H₃₉IrN₂O₂
 M.W. : 783.98 g/mole
 UV : 231, 301 nm (in CH₂Cl₂)
 PL : 628 nm (in CH₂Cl₂)
 TGA : > 310 °C (0.5% weight loss)




LT-N749 | DCQTB

(E)-2-(2-tert-Butyl-6-(2-(2,6,6-trimethyl-2,4,5,6-tetrahydro-1H-pyrrolo[3,2,1-ij]quinolin-8-yl)vinyl)-4H-pyran-4-ylidene)malononitrile

CAS No. : 953079-91-9
 Grade : > 98% (HPLC)
 Formula : C₂₈H₃₁N₃O
 M.W. : 425.57 g/mole
 UV : 485 nm (in THF)
 PL : 629 nm (in THF)
 TGA : > 340 °C (0.5% weight loss)


Reference : *Adv. Funct. Mater.* 2007, 17, 93-100



LT-N751 | Hex-Ir(piq)₂(acac)

Bis[(4-n-hexylphenyl)isoquinoline](acetylacetonate) iridium (III)


CAS No. : 435294-13-6
 Grade : > 99% (HPLC)
 Formula : C₄₇H₅₁IrN₂O₂
 M.W. : 868.22 g/mole
 UV : 301, 346 nm (in CH₂Cl₂)
 PL : 612 nm (in CH₂Cl₂)
 TGA : > 200 °C (0.5% weight loss)



LT-N752 | PtOEP

Platinum(II) octaethylporphine

CAS No.	: 31248-39-2
Grade	: > 95% (HPLC)
Formula	: $C_{36}H_{44}N_4Pt$
M.W.	: 727.84 g/mole
UV	: 389, 534 nm (in CH_2Cl_2)
PL	: 649 nm (in CH_2Cl_2)
TGA	: > 290 °C (0.5% weight loss)




LT-N753 | Ir(MDQ)₂(acac)

Bis(2-methylidibenzo[*f,h*]quinoxaline)(acetylacetonate) iridium(III)

CAS No.	: 536755-34-7
Grade	: Sublimed, > 99% (HPLC)
Formula	: $C_{39}H_{29}IrN_4O_2$
M.W.	: 777.88 g/mole
UV	: 325, 428 nm (in CH_2Cl_2)
PL	: 616 nm (in CH_2Cl_2)
TGA	: > 290 °C (0.5% weight loss)

Reference : *Adv. Mater.* 2003, 15, 3, p224-228




LT-N754 | Hex-Ir(piq)₃

Tris[2-(4-*n*-hexylphenyl)quinoline]iridium(III)

CAS No.	: 1240249-29-9
Grade	: > 99% (HPLC)
Formula	: $C_{63}H_{66}IrN_3$
M.W.	: 1057.43 g/mole
UV	: 325 nm (in CH_2Cl_2)
PL	: 617 nm (in CH_2Cl_2)
TGA	: > 250 °C (0.5% weight loss)


Reference : *Synthetic Metals* 161 (2011) 148-152



LT-N757 | Ir(dmpq)₃

Tris(2-(3-methylphenyl)-7-methyl-quinolato)iridium

Grade	: Sublimed, > 99% (HPLC)
Formula	: $C_{51}H_{42}IrN_3$
M.W.	: 889.12 g/mole
TGA	: > 280 °C (0.5% weight loss)




LT-N758 | PO-01-TB

Iridium(III) bis(4-(4-*tert*-butylphenyl) thieno[3,2-*c*]pyridinato-*N,C2'*) acetylacetonate

CAS No.	: 1267497-10-8
Grade	: Sublimed, > 99% (HPLC)
Formula	: $C_{39}H_{39}IrN_2O_2S_2$
M.W.	: 824.21 g/mole
UV	: 448 nm (in CH_2Cl_2)
PL	: 562 nm (in CH_2Cl_2)
TGA	: > 250 °C (0.5% weight loss)

Reference : 1. *TW 1395804, US 8,722,207*;
2. *Organic Electronics*, 2012, 13, 2149-2155 ;
3. *Mater. Chem. C*, 2013, 1, 5008-5014




LT-N762 | Ir(dmpq)₂acac

Bis[2-(2-methylphenyl)-7-methyl-quinoline](acetylacetonate)iridium(III)

CAS No.	: 909542-64-9
Grade	: Sublimed, > 99% (HPLC)
Formula	: $C_{39}H_{35}IrN_2O_2$
M.W.	: 755.92 g/mole
UV	: 273, 348 nm (in CH_2Cl_2)
PL	: 600 nm (in CH_2Cl_2)
TGA	: > 320 °C (0.5% weight loss)

Reference : *Thin Solid Films* 496 (2006)626-630




LT-N765 | FPQIrpic

Iridium(III) bis(2-(2,4-difluorophenyl)quinoline) picolinate

CAS No. : 1621179-34-7
 Grade : > 99% (HPLC)
 Formula : $C_{36}H_{14}F_4IrN_3O_2$
 M.W. : 795.11 g/mole
 UV : 342 nm (in THF)
 PL : 554 nm (in THF)
 TGA : > 270 °C (0.5% weight loss)


Reference : *Organic Electronics* (2013), 14(6), 1504-1509



LT-N766 | Ir(2-BtcPh)₂(pic)

Bis[2-(9-phenylcarbazol-2-yl)-benzothiazole] iridium(III) picolinate

CAS No. : 1452824-22-4
 Grade : > 99% (HPLC)
 Formula : $C_{56}H_{34}IrN_5O_2S_2$
 M.W. : 1065.18 g/mole
 UV : 324 nm (in CH_2Cl_2)
 PL : 624 nm (in CH_2Cl_2)
 TGA : > 280 °C (0.5% weight loss)




LT-N767 | Ir(DMP)₃

Tris[3-(2,6-dimethylphenoxy)-6-phenylpyridazine] iridium(III)

CAS No. : 1542693-87-7
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{54}H_{45}IrN_6O_3$
 M.W. : 1018.19 g/mole
 UV : 250 nm (in CH_2Cl_2)
 PL : 552 nm (in CH_2Cl_2)

Reference : *RSC Advances* (2013), 3(1), 215-220




LT-N768 | Ir(mphmq)₂acac

Bis[2-(3,5-dimethylphenyl)-4-methyl-quinoline] (acetylacetonate)iridium(III)

CAS No. : 1228537-77-6
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{41}H_{39}IrN_2O_2$
 M.W. : 783.98 g/mole
 UV : 432, 568 nm (in CH_2Cl_2)
 PL : 601 nm (in CH_2Cl_2)
 TGA : > 220 °C (0.5% weight loss)

Reference : *Organic Electronics Volume 13, Issue 10, October 2012, Pages 1956-1961*



LT-N771 | PR-08

Grade : >99% (HPLC)
 UV : 254, 301, 523 nm (in CH_2Cl_2)
 PL : 593 nm (in CH_2Cl_2)
 TGA : >230 °C (0.5% weight loss)

Reference : *Applied Mechanics and Materials*, 2015, 748 57-61

LT-N777 | PO-08

Grade : > 99% (HPLC)
 UV : 258, 292, 413 nm (in CH_2Cl_2)
 PL : 558 nm (in CH_2Cl_2)
 TGA : > 260 °C (0.5% weight loss)

Reference : *Applied Mechanics and Materials*, 2015, 748 57-61

Organic Light Emitting Diode (OLED)


Red Dopant Materials

LT-N778 | ED

(E)-2-(2-(4-(Dimethylamino)styryl)-1-ethylquinolin-4(1H)-ylidene)malononitrile

CAS No. : 1415845-07-6
Grade : > 99% (HPLC)
Formula : $C_{24}H_{22}N_4$
M.W. : 366.4680 g/mole
UV : 430 nm (in THF)
PL : 594 nm (in THF)
TGA : > 250 °C (0.5% weight loss)

Reference : *ACS Appl. Mater. Interfaces* 2013, 5, 192




LT-N780 | Ir(ppy)₃-Bp

Tris[1,1':4',1''-terphenyl-2-(2-pyridinyl-κM)phenyl-κC]iridium

CAS No. : 1404192-47-7
Grade : > 99% (HPLC)
Formula : $C_{69}H_{48}IrN_3$
M.W. : 1111.36 g/mole
UV : 294 nm (in CH_2Cl_2)
PL : 520 nm (in CH_2Cl_2)
TGA : > 250 °C (0.5% weight loss)


Reference : *Advanced Functional Materials* (2012), 22(16), 3406-3413



LT-N792 | Ir(dmppy-ph)2tmd

Bis(2-(3,5-dimethylphenyl)-4-phenylpyridine)(2,2,6,6-tetramethylheptane-3,5-diketonate)iridium(III)

CAS No. : 2050041-61-5
Grade : Sublimed, >99 % (HPLC)
Formula : $C_{49}H_{51}IrN_2O_2$
M.W. : 892.18 g/mole
UV : 276,398,481 nm (in $CHCl_3$)



LT-E301 | Liq

8-Hydroxyquinolinolato-lithium


CAS No. : 25387-93-3
 Grade : Sublimed, > 99.5% (HPLC)
 Formula : C_9H_6NOLi
 M.W. : 151.09 g/mole
 UV : 261 nm (in THF)
 PL : 514 nm (in THF)
 TGA : > 350 °C (0.5% weight loss)



LT-E302 | TPBi

2,2',2''-(1,3,5-Benzinetriyl)-tris(1-phenyl-1H-benzimidazole)


CAS No. : 192198-85-9
 Grade : Sublimed, > 99.5% (HPLC)
 Formula : $C_{45}H_{30}N_6$
 M.W. : 654.76 g/mole
 UV : 305 nm (in THF)
 PL : 370 nm (in THF)
 TGA : > 350 °C (0.5% weight loss)



LT-E303 | PBD

2-(4-Biphenyl)-5-(4-tert-butylphenyl)-1,3,4-oxadiazole


CAS No. : 15082-28-7
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{24}H_{22}N_2O$
 M.W. : 354.44 g/mole
 UV : 305 nm (in THF)
 PL : 380 nm (in THF)
 TGA : > 210 °C (0.5% weight loss)



LT-E304 | BCP

2,9-Dimethyl-4,7-diphenyl-1,10-phenanthroline


CAS No. : 4733-39-5
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{26}H_{20}N_2$
 M.W. : 360.45 g/mole
 UV : 277 nm (in THF)
 PL : 386 nm (in THF)
 TGA : > 240 °C (0.5% weight loss)



LT-E305 | Bphen

4,7-Diphenyl-1,10-phenanthroline


CAS No. : 1662-01-7
 Grade : Sublimed, > 99.5%
 Formula : $C_{24}H_{16}N_2$
 M.W. : 332.4 g/mole
 UV : 272 nm (in THF)
 PL : 379 nm (in THF)
 TGA : > 240 °C (0.5% weight loss)



LT-E407 | BA1q

Bis(2-methyl-8-quinolinolato)-4-(phenylphenolato)aluminium

CAS No. : 146162-54-1
 Grade : Sublimed, > 99%
 Formula : $C_{32}H_{25}N_2O_3Al$
 M.W. : 512.53 g/mole
 UV : 259 nm (in THF)
 PL : 477 nm (in THF)
 TGA : > 230 °C (0.5% weight loss)



Organic Light Emitting Diode (OLED)


Electron Transport Layer / Hole Blocking Layer(ETL/HBL) Materials

LT-N821 | Bpy-OXD

1,3-Bis[2-(2,2'-bipyridine-6-yl)-1,3,4-oxadiazole-5-yl]benzene

CAS No. : 866117-19-3
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{30}H_{18}N_8O_2$
M.W. : 522.52 g/mole
UV : 276, 308 nm (in THF)
PL : 348 nm (in THF)
TGA : > 300 °C (0.5% weight loss)


Reference : *J. Mater. Chem.*, 2006, 16, 221-225



LT-N828 | BP-OXD-Bpy

6,6'-Bis[5-(biphenyl-4-yl)-1,3,4-oxadiazole-2-yl]-2,2'-bipyridyl


CAS No. : 1219827-28-7
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{38}H_{24}N_6O_2$
M.W. : 596.64 g/mole
UV : 319 nm (in THF)
PL : 372 nm (in THF)
TGA : > 350 °C (0.5% weight loss)



LT-N832 | DBzA

6-Methyl-2-(4-(9-(4-(6-methylbenzo[d]thiazol-2-yl)phenyl)anthracen-10-yl)phenyl)benzo[d]thiazole

CAS No. : 850018-19-8
Grade : Sublimed, > 99%
Formula : $C_{42}H_{28}N_2S_2$
M.W. : 624.82 g/mole
UV : 311, 376, 396 nm (in THF)
PL : 448 nm (in THF)
TGA : > 400 °C (0.5% weight loss)



LT-N836 | TAZ


3-(4-(Biphenyl)-4-phenyl-5-tert-butylphenyl-1,2,4-triazole

CAS No. : 150405-69-9
Grade : Sublimed, > 98% (HPLC)
Formula : $C_{30}H_{27}N_3$
M.W. : 429.56 g/mole
UV : 290 nm (in THF)
PL : 370 nm (in THF)
TGA : > 250 °C (0.5% weight loss)

Reference : 1. *Appl. Phys. Lett. Vol. 85, No. 21, 22*

November 2


2. *Appl. Phys. Lett. 87, 193501 (2005)*



LT-N837 | NTAZ

4-(Naphthalen-1-yl)-3,5-diphenyl-4H-1,2,4-triazole


CAS No. : 16152-10-6
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{24}H_{17}N_3$
M.W. : 347.41 g/mole
UV : 264 nm (in CH_2Cl_2)
PL : 367 nm (in CH_2Cl_2)
TGA : > 260 °C (0.5% weight loss)



LT-N843 | NBphen

2,9-Bis(naphthalen-2-yl)-4,7-diphenyl-1,10-phenanthroline

CAS No. : 1174006-43-9
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{44}H_{28}N_2$
M.W. : 584.71 g/mole
UV : 264, 349 nm (in THF)
PL : 412 nm (in THF)
TGA : > 340 °C (0.5% weight loss)




Organic Light Emitting Diode (OLED)

Electron Transport Layer / Hole Blocking Layer(ETL/HBL) Materials

LT-N851 | Bpy-FOXO

2,7-Bis[2-(2,2'-bipyridine-6-yl)-1,3,4-oxadiazole-5-yl]-9,9-dimethylfluorene

CAS No. : 1174006-45-1
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{39}H_{26}N_8O_2$
M.W. : 638.68 g/mole
UV : 348, 365 nm (in CH_2Cl_2)
PL : 399 nm (in CH_2Cl_2)
TGA : > 350 °C (0.5% weight loss)




LT-N855 | OXD-7

1,3-Bis[2-(4-tert-butylphenyl)-1,3,4-oxadiazole-5-yl]benzene

CAS No. : 138372-67-5
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{30}H_{30}N_4O_2$
M.W. : 478.58 g/mole
UV : 292 nm (in THF)
PL : 347 nm (in THF)
TGA : > 290 °C (0.5% weight loss)

Reference : 1. JP Journal of Appl. Phys. Vol.44, No.6A, 2005,
2. Organic Electronics, Vol. 4, Issues 2-3, Sep. 2




LT-N856 | 3TPYMB

Tris(2,4,6-trimethyl-3-(pyridin-3-yl)phenyl)borane

CAS No. : 929203-02-1
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{42}H_{42}BN_3$
M.W. : 599.61 g/mole
UV : 331 nm (in THF)
PL : 382 nm (in THF)
TGA : > 230 °C (0.5% weight loss)


Reference : Chemistry Letters. Vol. 36, No. 2, P262, 2007.



LT-N857 | 2-NPIP

1-Methyl-2-(4-(naphthalen-2-yl)phenyl)-1H-imidazo[4,5f][1,10]phenanthroline


CAS No. : 1234997-42-2
Grade : Sublimed, > 99%
Formula : $C_{30}H_{20}N_4$
M.W. : 436.51 g/mole
UV : 275 nm (in CH_2Cl_2)
PL : 412 nm (in CH_2Cl_2)
TGA : > 360 °C (0.5% weight loss)



LT-N860 | HNBphen

2-(Naphthalen-2-yl)-4,7-diphenyl-1,10-phenanthroline


CAS No. : 923972-84-3
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{34}H_{22}N_2$
M.W. : 458.55 g/mole
UV : 281,327 nm (in CH_2Cl_2)
PL : 398 nm (in CH_2Cl_2)
TGA : > 320 °C (0.5% weight loss)



LT-N861 | POPy₂


Phenyl-dipyrenylphosphine oxide

CAS No. : 721969-93-3
Grade : Sublimed, > 99% (HPLC)
Formula : $C_{38}H_{23}OP$
M.W. : 526.56 g/mole
UV : 281, 360 nm (in CH_2Cl_2)
PL : 382 nm (in CH_2Cl_2)
TGA : > 370 °C (0.5% weight loss)
Reference : Appl. Phys. Lett. 92, 063306 2008




LT-N862 | BP4mPy3,3',5,5'-Tetra(*m*-pyridyl)-phen-3-yl]biphenyl

CAS No. : 1009033-94-6
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{56}H_{38}N_4$
 M.W. : 766.93 g/mole
 UV : 253 nm (in THF)
 PL : 352 nm (in THF)
 TGA : > 370 °C (0.5% weight loss)

Reference : *Org. Lett.*, 2008, 10(5), p941-944.**LT-N863** | TmPyPB


1,3,5-Tri(3-pyridyl)-phen-3-yl]benzene

CAS No. : 921205-03-0
 Grade : Sublimed, > 99.5%
 Formula : $C_{39}H_{27}N_3$
 M.W. : 537.65 g/mole
 UV : 254 nm (in CH_2Cl_2)
 PL : 353 nm (in CH_2Cl_2)
 TGA : > 310 °C (0.5% weight loss)

Reference : *Adv.Mater.*, 2008, 20, p2125-2130.**LT-N864** | BTB


4,4'-Bis(4,6-diphenyl-1,3,5-triazin-2-yl)biphenyl

CAS No. : 266349-83-1
 Grade : Sublimed product
 Formula : $C_{42}H_{28}N_6$
 M.W. : 616.71 g/mole
 TGA : > 360 °C (0.5% weight loss)

Reference : *Organic Electronics*, 2008, 9(3), p285**LT-N865** | BmPyPhB


1,3-Bis[3,5-di(pyridin-3-yl)phenyl]benzene

CAS No. : 1030380-38-1
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{38}H_{26}N_4$
 M.W. : 538.64 g/mole
 UV : 250 nm (in CH_2Cl_2)
 PL : 357 nm (in CH_2Cl_2)
 TGA : > 350 °C (0.5% weight loss)

Reference : *Chem. Mater.* 2008, 20, 5951-5953**LT-N868** | Bepq₂


2-(4-(9,10-Di(naphthalen-2-yl)anthracen-2-yl)phenyl)-1-phenyl-1H-phenanthro[9,10-d]imidazole

CAS No. : 148896-39-3
 Grade : Sublimed product
 Formula : $C_{26}H_{16}BeN_2O_2$
 M.W. : 397.43 g/mole
 UV : 406 nm (in CH_2Cl_2)
 PL : 492 nm (in CH_2Cl_2)
 TGA : > 320 °C (0.5% weight loss)

**LT-N869** | DPPS

Diphenylbis(4-(pyridin-3-yl)phenyl)silane

CAS No. : 1152162-74-7
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{34}H_{26}N_2Si$
 M.W. : 490.67 g/mole
 UV : 251 nm (in CH_2Cl_2)
 PL : 366 nm (in CH_2Cl_2)
 TGA : > 230 °C (0.5% weight loss)


Reference : *Adv. Mater.* 2009, 21, 1271-1274

LT-N870 | PY1

3,5-Di(pyren-1-yl)pyridine

CAS No. : 1246467-58-2
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{37}H_{21}N$
 M.W. : 479.57 g/mole
 UV : 246, 282, 351 nm (in CH_2Cl_2)
 PL : 389 nm (in CH_2Cl_2)
 TGA : > 390 °C (0.5% weight loss)

Reference : *Organic electronics*, 10, (2009), 877-882




LT-N878 | PFNBr

Poly[(9,9-bis(3'-((N,N-dimethyl)-N-ethylammonium)-propyl)-2,7-fluorene)-alt-2,7-(9,9-dioctylfluorene)]

Grade : $M_w > 10,000$ (GPC)
 Formula : $(C_{56}H_{80}N_2Br_2)_n$
 UV : 375 nm (in MeOH)
 PL : 440 nm (in MeOH)
 Solubility : Soluble in MeOH

Reference : *Chem. Mater.*, 2004, 16, 708




LT-N879 | TPyQB

1,3,5-Tris(4-(pyridin-4-yl)quinolin-2-yl)benzene

CAS No. : 1350742-68-5
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{48}H_{30}N_6$
 M.W. : 690.79 g/mole
 PL : 381 nm (in CH_2Cl_2)
 TGA : > 400 °C (0.5% weight loss)


Reference : *Advanced Functional Materials* (2011), 21(20), 3889-3899.



LT-N885 | BIPO

2,2'-(4,4'-(Phenylphosphoryl)bis(4,1-phenylene))bis(1-phenyl-1H-benzo[d]imidazole)

CAS No. : 1426143-77-2
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{44}H_{31}N_4OP$
 M.W. : 662.72 g/mole
 UV : 309 nm (in CH_2Cl_2)
 PL : 379 nm (in CH_2Cl_2)
 TGA : > 250 °C (0.5% weight loss)




LT-N887 | Libpp

Lithium 2-(2',2''-bipyridine-6'-yl)phenolate

CAS No. : 1049805-81-3
 Grade : Sublimed, > 99% (NMR)
 Formula : $C_{16}H_{11}LiN_2O$
 M.W. : 254.21 g/mole
 UV : 235, 265 nm (in CH_2Cl_2)
 PL : 345 nm (in CH_2Cl_2)
 TGA : > 220 °C (0.5% weight loss)

Reference : *Organic Electronics* (2009), 10(2), 228-232




LT-N889 | Tm3PyP26PyB

1,3,5-Tris(6-(3-(pyridin-3-yl)phenyl)pyridin-2-yl)benzene

CAS No. : 1492917-78-8
 Grade : Sublimed, > 99% (NMR)
 Formula : $C_{54}H_{36}N_6$
 M.W. : 768.9 g/mole
 UV : 255 nm (in CH_2Cl_2)
 PL : 357 nm (film)
 TGA : > 280 °C (0.5% weight loss)

Reference : *Advanced Functional Materials* (2014), 24(21), 3268-3275




LT-N890 | B3PYPPM

4,6-Bis(3,5-di(pyridin-3-yl)phenyl)-2-(pyridin-3-yl)pyrimidine

CAS No. : 1382639-67-9
 Grade : Sublimed, > 99% (NMR)
 Formula : $C_{41}H_{27}N_7$
 M.W. : 617.7 g/mole
 UV : 255 nm (in CH_2Cl_2)
 TGA : > 280 °C (0.5% weight loss)


Reference : *Chemistry of Materials* (2012), 24(20), 3817-3827

**LT-N891** | B4PYPPyPM

4,6-Bis(3,5-di(pyridin-4-yl)phenyl)-2-(3-(pyridin-3-yl)phenyl)pyrimidine

CAS No. : 1382639-70-4
 Grade : Sublimed, > 99% (NMR)
 Formula : $C_{47}H_{31}N_7$
 M.W. : 693.8 g/mole
 UV : 255 nm (in CH_2Cl_2)
 TGA : > 280 °C (0.5% weight loss)


Reference : *Chemistry of Materials* (2012), 24(20), 3817-3827

**LT-N892** | TP3PO


1,3,5-Tri(diphenylphosphoryl)phen-3-yl) benzene

CAS No. : 1311378-95-6
 Grade : Sublimed, > 98% (HPLC)
 Formula : $C_{60}H_{45}O_3P_3$
 M.W. : 906.92 g/mole
 UV : 259 nm (in CH_2Cl_2)
 PL : 349 nm (in CH_2Cl_2)
 TGA : > 250 °C (0.5% weight loss)

Reference : *Chemistry of Materials* (2014), 26(3), 1463-1470


**LT-N894** | FPQ-BrPoly[9,9-bis[6'-(*N,N,N*-trimethylammonium)hexyl]fluorene-*alt-co*-1,4-phenylene]bromide

Grade : $M_w > 20,000$ (GPC)
 Formula : $(C_{37}H_{52}Br_2N_2)_n$
 Reference : *Adv Mate.* 2011, V23, 2759-2763

**LT-N895** | NaQ

8-Hydroxyquinoline sodium salt


CAS No. : 2872-54-0
 Grade : Sublimed, > 99% (HPLC)
 Formula : C_9H_6NONa
 M.W. : 167.14 g/mole
 UV : 261 nm (in THF)
 PL : 331 nm (in THF)
 TGA : > 310 °C (0.5% weight loss)



LT-N8001 | DBimiBphen

4,7-Diphenyl-2,9-bis(4-(1-phenyl-1*H*-benzo[d]imidazol-2-yl)phenyl)-1,10-phenanthroline


CAS No. : 1447848-17-0
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{62}H_{40}N_6$
 M.W. : 869.02 g/mole
 UV : 319, 357 nm (in CH_2Cl_2)
 TGA : > 400 °C (0.5% weight loss)



LT-N8002 | BimiBphen

4,7-Diphenyl-2-(4-(1-phenyl-1*H*-benzo[d]imidazol-2-yl)phenyl)-1,10-phenanthroline


Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{43}H_{28}N_4$
 M.W. : 600.71 g/mole
 TGA : > 350 °C (0.5% weight loss)



LT-N8004 | TPM-TAZ


2,4,6-Tris(3-(pyrimidin-5-yl)phenyl)-1,3,5-triazine

CAS No. : 1874199-82-2
 Grade : Sublimed, > 99% (HPLC)
 Formula : $C_{33}H_{21}N_9$
 M.W. : 543.58 g/mole




LT-N8006 | PFN-diiodine salt

Formula : $(C_{56}H_{60}N_2I_2)_n$



LT-N8007 | PFN-B-diiodine salt

Formula : $(C_{31}H_{40}I_2N_2)_n$



Organic Light Emitting Diode (OLED)

Electron Injection Layer(EIL) Materials / Metal

LT-E001 | LiF

Lithium fluoride

CAS No. : 7789-24-4
Grade : > 99.99%
Formula : LiF
M.W. : 25.94 g/mole
Melting Point : 848 °C
Boiling Point : 1681 °C

LT-E002 | Cs₂CO₃

Cesium carbonate

CAS No. : 534-17-8
Grade : > 99.994%
Formula : Cs₂CO₃
M.W. : 325.82 g/mole
Melting Point : 610 °C

LT-E003 | MoO₃

Molybdenum(VI) Oxide

CAS No. : 1313-27-5
Grade : > 99.998%
Formula : MoO₃
M.W. : 143.94 g/mole
Melting Point : 795 °C

LT-E004 | CsF

Cesium fluoride

CAS No. : 13400-13-0
Grade : > 99%
Formula : CsF
M.W. : 151.90 g/mole
Melting Point : 682 °C

LT-E005 | Al


Aluminium

CAS No. : 7429-90-5
Grade : > 99.999%
Formula : Al
M.W. : 26.98 g/mole
Melting Point : 660 °C

LT-E007 | Rb₂CO₃

Rubidium carbonate

CAS No. : 584-09-8
Grade : > 99.9%
Formula : Rb₂CO₃
M.W. : 588.74 g/mole



LT-E008 | ReO₃

Rhenium(VI) oxide

CAS No. : 1314-28-9
Grade : > 99.9%
Formula : ReO₃
M.W. : 234.21 g/mole

