

Innovaprene® F 60



FOOD PROCESS TUBING

For critical processing applications in the food, beverage, dairy and cosmetic industries.

Food

FDA 21CFR 177.2600



Innovaprene® F 60

Ideal for use in CIP/SIP cleaning systems and compatible with all commercial cleaners and sanitizers. F60 fully complies with FDA 21CFR 177.2600 criteria and NSF standard 51, which are applicable in many food contact applications. F60 food process tubing provides superior resistance to many corrosive fluids and also shows good resistance to the animal and vegetable oil.

Features

- Long pump life
- Food contact
- Stable flow rate
- Chemical resistance
- UV resistance
- Low gas and vapor permeable
- Wide temperature range -60 to 135C

Regulations

FDA 21CFR 177.2600
EC No 1935/2004*

*Innovaprene FW

Applications

- Cosmetic production
- Food and dairy processing
- Hot beverage dispensing
- Water purification lines
- Sanitizer delivery
- Soap dispensing
- Pesticide and fertilizer delivery



+86 (0)512 58637230
+86 17321382507



info@innovapure.com
www.innovapure.com



Innovation Park, Leyu town
Zhangjiagang, Suzhou, China

Innovaprene® F 60 inventoried sizes

Model #	Tube #	I.D.		O.D.		Wall thickness		Length / Box*	
		(mm)	(Inch)	(mm)	(Inch)	(mm)	(Inch)	(M)	(Feet)
PF60-201-0100-0300		1.00		3.00		1.00		15.2	50
PF60-201-0159-0476	14#	1.59	1/16	4.76	3/16	1.59	1/16	15.2	50
PF60-201-0238-0556	19#	2.38	3/32	5.56	7/32	1.59	1/16	15.2	50
PF60-201-0318-0635	16#	3.18	1/8	6.35	1/4	1.59	1/16	15.2	50
PF60-201-0318-0794	120#	3.18	1/8	7.94	5/16	2.38	3/32	15.2	50
PF60-201-0476-0794	25#	4.76	3/16	7.94	5/16	1.59	1/16	15.2	50
PF60-201-0476-0953	15#	4.76	3/16	9.53	3/8	2.38	3/32	15.2	50
PF60-201-0635-0953	17#	6.35	1/4	9.53	3/8	1.59	1/16	15.2	50
PF60-201-0635-1111	24#	6.35	1/4	11.11	7/16	2.38	3/32	15.2	50
PF60-201-0794-1111	18#	7.94	5/16	11.11	7/16	1.59	1/16	15.2	50
PF60-201-0794-1270	35#	7.94	5/16	12.70	1/2	2.38	3/32	15.2	50
PF60-201-0953-1270	96#	9.53	3/8	12.70	1/2	1.59	1/16	15.2	50
PF60-201-0953-1429	36#	9.53	3/8	14.29	9/16	2.38	3/32	15.2	50
PF60-201-0953-1588	73#	9.53	3/8	15.88	5/8	3.18	1/8	15.2	50
PF60-201-1111-1429		11.11	7/16	14.29	9/16	1.59	1/16	15.2	50
PF60-201-1270-1905	82#	12.70	1/2	19.05	3/4	3.18	1/8	15.2	50

*Other sizes and length can be customized

Innovaprene® F 60 typical physical properties

Physical Properties	Test Method	Unit	Typical Value
Color	-		Natural
Shore A, 5 sec.	ISO 868		67
Specific gravity	ISO 2781		0.97
Working temperature		C	-60 to 150
UV resistance			Excellent
Vapor permeability			Fair
Moisture absorption			Low
Tensile strength	ISO 37-2005	Mpa	6.80
Elongation at 100%	ISO 37-2005	%	500
Tear strength	D1004-94	kN/m	22
Compression set, 70C 22hrs.	D395-98-B	%	18
Brittle temperature	ISO 812	C	-60

Innovaprene® F 60 chemical compatibility chart is available on www.innovapure.com or call Innovapure sales representative.

Distributed by

HONDWEN CO., LTD.
TEL: +886-227928751
www.hondwen.com.tw



Important

It is the user's responsibility to ensure the suitability and safety of Suzhou Innovapure Co., Ltd. products for all intended uses. Laboratory and clinical tests must be conducted in accordance with applicable regulatory requirements in order to determine the safety and effectiveness for use of tubing in any particular application.